



MP5405

MP5405 is a two part unfilled epoxy adhesive designed for ceramics, and most plastics. It cures to a tough semi-rigid material, and is a free flowing viscosity. It gives good resistance to water, salt spray, inorganic acids and bases, and most organic solvents. It was especially formulated to a 1:1 mix ratio for use in either MMD equipment or side-by-side dual cartridges for easy dispensing. Handling strength is normally achieved at room temperature within 3-5 minutes with full cure in 24 hours. An elevated temperature cure schedule can be used to reach final properties quickly.

Technology / Base	Epoxy
Type of Product	Structural Adhesive
Components	Two Component
Curing	Room Temperature (secondary thermal cure)
Appearance / Color	Clear
Consistency	Liquid

Features and Benefits

- Excellent Adhesion Properties
- Excellent Bonding to Metals, Ceramics and Most Plastics
- Excellent Chemical Resistance
- Suitable for Cartridge and MMD Dispensing Equipment
- Excellent Thermal Performance
- 100% Reactive
- Room Temperature Cure
- 1:1 volume mix product for easy meter or static mix of application

Technical Data

Rheology	Value	Condition/Method
Viscosity - Part A	12,000 cPs	at 25°C
Viscosity - Part B	13,000 cPs	at 25°C
Viscosity - Mixed	12,500 cPs	at 25°C
Uncured Material Characteristics		
Specific Gravity - Part A	1.16	
Specific Gravity - Part B	1.15	
Specific Gravity - Mix	1.16	
Volume Mix Ratio	1 to 1	
Weight Mix Ratio	1 to 1	
Pot Life	3 to 5 min	at 25°C
Gel Time		20 gram
Handling Time	3 to 5 min	20 gram
Full Cure @ 23°C	24 hours	
Full Cure @ 66°C		
Shelf Life	12 months unopened	
Cured Mechanical Properties		
Hardness	80 Shore D	ASTM D2240
Tensile Strength	48.3 MPa (7000 psi)	ASTM D638
Elongation at Break	3 to 5 %	ASTM D638
Overlap Shear Strength		
Aluminum, Acid Etched at 25°C	15.9 MPa (2300 psi)	ASTM D1002, 25°C 50% RH
Operating Temperature	-40°C to 130°C (-40°F to 265°F)	
Cured Electrical Properties		
Dielectric Constant	4.5 at 25°C, 100Hz	ASTM D150
Dielectric Strength	16.1 kV/mm	ASTM D149
Volume Resistivity	8 E 14 ohm-cm	ASTM D257



General Instructions

Surfaces to be bonded must be clean, dry and free of other contaminants. Bring both components to room temperature prior to mixing. Measure out specified amounts of parts A and B and mix without introducing bubbles until homogenous. Alternately use a static mixing nozzle. Apply to device allowing air to escape between and under components. Allow to cure undisturbed until product is fully gelled or tack-free to the touch.

H.B. Fuller Company, ASI
 9411 Corsair Road
 Frankfort, IL 60423
 +1.815.464.5606 tel

www.hbfuller.com

www.hbfullerengineering.com

Date Modified: 14 September 2018

Connecting what matters.™

IMPORTANT: Information, specifications, procedures and recommendations provided ("information") are based on our experience, and we believe this information to be accurate. No representation, guarantee or warranty is made as to the accuracy or completeness of the information or that use of the product will avoid losses or damages or give desired results. It is purchaser's sole responsibility to test and determine the suitability of any product for the intended use. Tests should be repeated if materials or conditions change in any way. No employee, distributor or agent has any right to change these facts and offer a guarantee of performance.

® and ™ are trademarks of H.B. Fuller Company or one of its affiliated entities.

NOTE TO USER: by ordering/receiving product you accept the **H.B. Fuller General Terms and Conditions of Sale** applicable in the region. Please request a copy if you have not received these. These Terms and Conditions contain disclaimers of implied warranties (including but not limited to disclaiming warranties of fitness for a particular purpose) and limits of liability. All other terms are rejected. In any event, the total aggregate liability of H.B. Fuller for any claim or series of related claims however arising, in contract, tort (including negligence), breach of statutory duty, misrepresentation, strict liability or otherwise, is limited to replacement of affected products or refund of the purchase price for affected products. H.B. Fuller shall not be liable for loss of profit, loss of margin, loss of contract, loss of business, loss of goodwill or any indirect or consequential losses arising out of or in connection with product supply.

Specifications and Approvals

Handling and Clean-Up

See SDS for handling and clean-up information.

Storage

Product should be stored in a cool dry place out of direct sunlight. The shelf life is from date of manufacture. Shelf life is based on the products being stored properly at temperatures between 12°C and 25°C. Exposure to temperatures above 25°C will reduce the shelf life. This product should not be frozen.

Use Note

Safety and Disposal

See SDS for



H.B. Fuller
www.hbfuller.com

©H.B. Fuller Company, 2019