



CORPORATE HEADQUARTERS 5700 Skylab Road

Huntington Beach, California 92647 Phone: (714) 899-8100

Fax: (714) 899-8179

Internet: http://www.airtechonline.com

email: airtech@airtechintl.com

Page 18 2-28-97

Distributed By Freeman Manufacturing & Supply Co. FREEMAN www.freemansupply.com 800-321-8511

DATA SHEET

AIRTECH 1050

Silicone Rubber, Cured and Unsupported

Thermavac® Elastomeric Vacuum Bagging Materials

Description:

The Thermavac® grade silicone rubber is a proprietary formulation that offers high reversion resistance and strength. It is designed to provide superior performance in composite lamination systems for vacuum/autoclave and vacuum/hydraulic curing. Any silicone rubber has the potential to transfer. Silicone transfer investigation should be done by the user.

Available Forms: Thickness:

.040" (1.02mm) - .060" (1.52mm) 48" (122cm) <u>+</u> .25 (6.4mm) usable material Width:

(edges untrimmed)

Finish: Glossy Cured State:

25 LYD Roll (22.9m) Form:

Color:

Note: Rolls may contain one unbonded splice with a minimum length of 5 yards (4.6m). An additional yard will be added to a spliced roll at no additional cost on full roll orders.

Physical Properties:

<u>Property</u> Durometer	<u>Test Method</u> ASTM-D2240, Shore A	<u>Value</u> 50
Tear, lbs/in.	ASTM-D624, Die B (75°F) (212°F)	250 200
Tensile, psi	ASTM-D412, Die A	1400
Elongation %	ASTM-D412, Die A	700
100% Modulus, psi		300
300% Modulus, psi		250
Temperature Use Range		600°F
Coefficient of Thermal Expansion	in/in/°F (75°F-350°F)	1.6 x 10 ⁻⁴
Compression Set	ASTM-D395, Method B 22 hrs. 350°F	28%
Volumetric Expansion	in/in/°F (75°F-350°F)	5 x 10 ⁻⁴
Thermal Conductivity	ASTM-F433 325°F BTU-in./FT² hr.°F	1.8

CATALOG POSITION: RUBBER



As the conditions or methods of use are beyond our control, Airtech International, Inc. does not assume any responsibility for the performance of this material for any particular use. The material is sold "as is". Airtech International, Inc. disclaims, and buyer waives, any and all implied warranties, including without limitation the implied warranties of merchantability and of fitness for particular use.