



FREEMAN
Manufacturing & Supply Co.

1101 Moore Rd.
Avon, OH 44011

Phone 800 321 8511
Fax 440 934 7200
www.freemansupply.com

Atlanta, GA
800 445 0811

Detroit, MI
800 345 9259

Fort Worth, TX
800 792 1047

Harrisburg, PA
800 631 4230

Los Angeles, CA
800 325 2100

Milwaukee, WI
800 558 0866

Montreal, QC
800-263-7699

Portland, OR
800 558 0866

St. Paul, MN
800 558 0866

Toronto, ON
800 345 9259

Wichita, KS
800 792 1047

MiaGel F-944

Neutral Polyester Gelcoat

Description

MiaGel F-944 is neutral in color, enabling the user to custom color this product as desired. Use polyester color pastes only. MiaGel F-944 is specifically designed for making high quality fiberglass reinforced molds and parts. Applied using spray equipment, this product is sag resistant and fast curing. This room temperature curing product should be catalyzed with methyl ethyl ketone peroxide (MEKP).

Physical Properties

Color	Neutral
Mix Ratio (by wt)	1.2 to 3.0% (1.8% recommended)
Viscosity (cps)	11,000 - 16,000
Gel Time	10-17
Demold time (hours)	24

Ordering Information

Item Number	Description	Net Wt.
411760	MiaGel F-944 Resin Gallon	8.8 lbs (4 kg)
412161	MEKP Liquid Hardener 0.75 fl.oz.	0.125 lbs (0.06 kg)

Designated mix ratios must be adhered to for desired results. The user shall determine the suitability of this product for their application and assumes all risks and liabilities associated with the use of this product. The exclusive remedy for all proven claims is replacement of our materials only and in no event shall Freeman Mfg. & Supply Co. be liable for special, incidental, or consequential claims.

READ SAFETY DATA SHEETS AND PRODUCT LABELS BEFORE USING PRODUCT

Freeman Mfg. & Supply Co.

1101 Moore Rd.
Avon, Ohio 44011
www.freemansupply.com
800-321-8511