



## MiaGel F-944 Neutral Polyester Gelcoat

### Description

MiaGel F-944 is neutral in color, enabling the user to custom color this product as desired. Use polyester color pastes only. MiaGel F-944 is specifically designed for making high quality fiberglass reinforced molds and parts. Applied using spray equipment, this product is sag resistant and fast curing. This room temperature curing product should be catalyzed with methyl ethyl ketone peroxide (MEKP).

### Physical Properties

Color	Neutral
Mix Ratio (by wt)	1.2 to 3.0% (1.8% recommended)
Viscosity (cps)	11,000 – 16,000
Gel Time (minutes)	10-17
Demold Time (hours)	24

### Ordering Information

SKU	Description	Size	Net wt.
411760	MiaGel F-944 Resin Gallon	Gallon	8.8 lbs
412162	MEKP Liquid Hardener 1 oz.	1 oz.	1 oz.

The user shall determine the suitability of this product for their application and assumes all risks and liabilities associated with the use of this product. The exclusive remedy for all proven claims is replacement of our materials only and in no event shall Freeman Mfg. & Supply Co. be liable for special, incidental, or consequential claims.

READ SAFETY DATA SHEETS AND PRODUCT LABELS BEFORE USING PRODUCT

