



Product Data

RenCast™ 6498/Ren® 6498 Flexible Polyurethane System

DESCRIPTION: RenCast™ 6498/Ren® 6498, a non-mercury, flexible polyurethane system. This product is a new development in the family of RenCast fast polyurethanes, which have been specially formulated to have an interesting combination of long work time (gel time) and short demolding time. RenCast 6498 is designed to produce rubber-like parts with flexibility and hardness of 80-90 Shore A.

APPLICATIONS:

- Handcasting
- Vacuum Casting
- Pressure Pot Casting

ADVANTAGES:

- Contains no mercury catalyst
- Convenient mix ratio
- Can be used in a broad range of processes
- Neutral color makes this system pigmentable

MIXING INSTRUCTIONS:

Reaction Ratio 50R to 100H by weight
 45R to 100H by volume

TYPICAL MIXED PROPERTIES:

Color	Amber
Reaction Ratio, by weight	50R/100H
Mixed Viscosity, cp	1700 cps @ 2 min
Gel Time 150 gm mass	5 - 6 min
Demold Time (depending upon part thickness and geometry)	2 hours @ RT 0.5 (30 minutes) @ 140F

TYPICAL CURED PROPERTIES:

Cured Color	Amber
Hardness	85 Shore A
Tensile Strength	950 psi
% Elongation at Break	180%
Tear Strength	180 ppi

STORAGE/HANDLING INFORMATION: Store at 70° - 90°F. This product is moisture sensitive and packaged under a blanket of dry nitrogen. Maintain factory seal. After use reblanket with nitrogen and tightly reseal. This product may crystallize upon storage. If crystallized, vent container and heat to 125° - 145°F until crystals dissolve. Stir well after product has liquefied. If heating of products in plastic packaging is necessary, heat in a ventilated oven to 145°F maximum. Before heating loosen the container lid slightly to relieve any pressure buildup and place container to be heated into a metal bucket of sufficient volume to contain the product, should the container tip over or leak. Work in a well ventilated area and use clean, dry tools for mixing and applying.

Combine the resin and hardener according to mix ratio, mix together thoroughly and use immediately after mixing. Material temperature should not be below 65°F (18°C) when mixing.

SHELF LIFE: Provided materials are stored under the recommended storage conditions in their original containers, they will remain in useable condition for at least six months from date of shipping.

PACKAGING: This product is available in the following package sizes:

Prewriteghed gallon kit (12# total) contains 4# of resin base and 8# of hardener catalyst and 5-gallon pails containing 20# of resin base and 40# of hardener catalyst

Please call Customer Service (800) 367-8793 for price and availability

SAFETY/HANDLING PRECAUTIONS: Do not use or handle this product until the Material Safety Data Sheet has been read and understood.

FIRST AID: In case of contact with:

Skin: Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. Destroy contaminated shoes.

Eyes: Immediately flush with water for at least 15 minutes. Call a physician.

Ingestion: If conscious, give 2-4 glasses of water to drink. Do not induce vomiting. Call a physician.

Inhalation: Remove to fresh air. Call a physician.

PRECAUTIONARY NOTE: Thermosetting systems generate heat when curing. The amount of heat and the period of time in which heat is released vary significantly between systems. Additionally, ambient or compound temperature, amount of material mixed, and construction and shape of the mold or container can also be factors in the temperature profile of a mixed system. In some cases, the thermosetting reaction can be vigorous, generating heat sufficient to cause decomposition of the system with subsequent liberation of large volumes of acrid smoke.

A good rule of thumb is never mix more material than can be applied during the stated pot life or gel time. Also take care when using materials in applications other than stated on the Product Data Sheet, i.e., a laminating resin for casting.

Please feel welcome to call our Product Information Department or your local Ren representative for instructions before you start your job.

IMPORTANT LEGAL NOTICE:
DISCLAIMER AND LIMITATION OF LIABILITY: SELLER MAKES NO WARRANTY OR REPRESENTATION, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. No statement or recommendation contained in any Product literature may be construed as a representation about the suitability of a Product for the particular application of Buyer or user or as an inducement to infringe any relevant patent. Seller neither assumes, nor authorizes any representative or other person to assume for it, any obligation or liability other than as is expressly set forth herein. **UNDER NO CIRCUMSTANCES SHALL SELLER BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL, SPECIAL OR OTHER INDIRECT DAMAGES AS A RESULT OF A BREACH OF ANY WARRANTY OR THE FAILURE OF A PRODUCT OR ANY CLAIM THAT IS ESSENTIALLY BASED UPON SUCH BREACH OR FAILURE.** Any claim by Buyer, whether arising in contract, tort, negligence, breach of warranty, strict liability, or otherwise, related to a Product shall be limited to, and the sole liability of Seller and the sole remedy of Buyer for any claims shall be for, the purchase price of the Product in respect of which such claim is made. The foregoing **DISCLAIMER and LIMITATION OF LIABILITY** supercedes Buyer's documents.
WARNING: Technical data and results are based upon tests under controlled laboratory conditions and must be confirmed by Buyer by testing for its intended conditions of use. The Product has not been tested for, and therefore is not recommended or suitable for, uses for which prolonged contact with mucous membranes, abraded skin, or blood is intended or likely, or for uses for which implantation within the human body is intended, and Huntsman assumes no liability for any such uses.