

Advanced Materials**RenCast[®] 4037 / Ren[®] 4037****HIGH-TEMPERATURE ALUMINUM FILLED CASTING SYSTEM****DESCRIPTION:**

RenCast[®]/Ren[®] 4037 is a non-MDA, MPDA, VCHD aluminum-filled epoxy casting system intended for use to 300°F (149°C). Intermittent use to 350°F (177°C) is possible. RenCast[®] /Ren[®] 4037 can be cast to 4" thick in nonconductive molds and 6" thick in conductive molds.

MIXING RATIO:

	By weight:	By Volume:
Resin to Hardener	100 to 13	100 to 22

TYPICAL HANDLING PROPERTIES*:

Property	ASTM Method	Resin	Hardener	Mixed
Color	Visual	Gray	Brown	Gray
Specific Gravity	D-1963	1.66 – 1.76	1.01 – 1.03	
Viscosity, cP	D-2393	39,600	400 – 700	15,000
Gel Time, 14 fl. oz, minutes	D(2471			140

NOTE: These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed in establishing product specifications, please consult with our Product Management Department.

RECOMMENDED CURE SCHEDULE:

- 77°F (25°C) at 24 hours, **plus**
 200°F (93°C) at 2 hours, **plus**
 250°F (121°C) at 2 hours, **plus**
 300°F (149°C) at 2 hours, **plus**
 350°F (177°C) at 2 hours

TYPICAL CURED PROPERTIES*:

Property	ASTM Test Method	Cure Values
Density, lb./ft ³ (g/cm ³)	D-792	(1.58)
Cubic Inch per Pound	D-792	17.6
Hardness, Shore D	D-2240	91
Ultimate Flexural Strength (psi)	D-790	9,300
Flexural Modulus, psi	D-790	930,000
Ultimate Tensile Strength, psi	D-638	6,300
T _g by DMA, E", °F (°C)	D-4065	350 (177)
Ultimate Compressive Strength, psi	D-695	25,800
Coefficient of Thermal Expansion 86 to 212°F, in/in/°F 30 to 100°C, in/in/°C	D-3386	22.5 x 10 ⁻⁶ 40.5 x 10 ⁻⁶
Linear Shrinkage, in/in	D-2566	0.005

* Tested @ 77°F (25°C) unless otherwise noted.

** Molds are half round steel, 10 inches long, 4.250 inches deep

NOTE: Typical Properties – These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed in establishing product specifications, please consult with our Quality Control Department.

STORAGE:

RenCast[®] 4037 and Ren[®] 4037 should be stored in a dry place, in the sealed original container, at temperatures between +2°C and +40°C (+35.6°F and 104°F). Under these storage conditions, the shelf life is 2 years. The product should not be exposed to direct sunlight.

PRECAUTIONARY STATEMENT:

Huntsman Advanced Materials Americas LLC maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to MSDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

IMPORTANT LEGAL NOTICE

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMITATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Ren is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2008 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Offices :

Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

Huntsman Advanced Technology Center

8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400
Website :
www.huntsman.com/advanced_materials