



BLUESIL™ V-243

Distributed By
Freeman Manufacturing & Supply Co.
www.freemansupply.com 800-321-8511



Addition Cure Silicone Elastomer

Description **BLUESIL™ V-243** is a two component, high strength, addition cure, silicone requiring a heat cure to obtain optimum properties. The long work life, high strength properties, and its ability to accept high levels of silicone diluent fluid, make it an excellent choice for transfer print pad applications. **BLUESIL™ V-243** is also an excellent product for roll applications.

Applications

- Transfer Print Pads
- Converter and embossing rolls
- Heat activated adhesive label rolls
- Hot melt glue rolls

Typical Properties

TYPICAL PROPERTIES - AS SUPPLIED		TYPICAL CATALYZED PROPERTIES	
Part A - Base Component		Mixed at 24°C (75°F) and 50% R.H.	
• Color	Beige	• Mix Ratio , A:B (Parts by weight)	10:1
• Consistency	Pourable	• Viscosity , cP. (mPa.s)	100,000
• Viscosity , cP. (mPa.s)	150,000	• Pot Life , hours ⁽¹⁾	5
• Specific Gravity	1.28	<i>Cure rolls for 3-4 hours at 150°C (300°F) to obtain a Shore Hardness of 60. Allow extra soak time for heat transfer through casing and core of roll.</i>	
Part B – Curing Agent			
• Color	Black		
• Specific Gravity	1.018		

⁽¹⁾ Time at which material gels.

TYPICAL PROPERTIES OF CURED RUBBER (Cured 1 hour at 150°C (300°F))		
Property	Test Method	Value
• Color	ASTM D2240	Beige
• Specific Gravity		1.24
• Hardness (Shore A)		60
• Coverage - cu. in/lb. (cc/kg)		22.5 (812)
• Temperature Range , °C (°F)		-54 to 204 (-65 to 400)

TRANSFER PRINT PAD FORMUATIONS - Cure 2 hrs at 185°F to 212°F (85°C to 100°C), pad thickness 1 inch			
Components	Parts by Weight	Shore (00)	
BLUESIL™ V-243A	100	50 (crown)	crown = curved surface of pad flat = flat surface of pad
BLUESIL™ V-243B	10	45 (flat)	
BLUESIL™ FLD 47V50	100		
BLUESIL™ V-243A	100	40 (crown)	
BLUESIL™ V-243B	10	35 (flat)	
BLUESIL™ FLD 47V50	130		
BLUESIL™ V-243A	100	35 (crown)	
BLUESIL™ V-243B	10	30 (flat)	
BLUESIL™ FLD 47V50	150		

Please note: The typical properties listed in this bulletin are not intended for use in preparing specifications for any particular application of BLUESIL™ silicone materials. Please contact our Technical Service Department for assistance in writing specifications.



Instructions for use

MIXING GUIDELINES FOR BLUESIL™ PLATINUM CURE MOLDMAKING SYSTEMS

1. Stir the base (Part A) well before use (except when machine dispensing).
2. Shake the curing agent container (Part B) well before use.
3. Weigh the desired amount of base into a clean mixing container. Tip the container and roll the base all the way around the side wall up to two inches from the top. This will prevent the curing agent from being absorbed into the container. Do not fill the container more than 1/3 full to allow sufficient room for expansion during the deaeration procedure.
4. Weigh the proper amount of curing agent into the container.
5. Mix the base and curing agent together by stirring with a stiff, flat ended metal spatula until a uniform color is obtained. Scrape the container walls and bottom to assure a thorough mix. If mechanical mixer is used, do not exceed 150 rpm.
6. Place the container into a vacuum chamber and evacuate the entrapped air from the mixture using a vacuum pump capable of achieving 29 inches of vacuum. The mixture will rise, crest and then collapse in the container. Interruption (bumping) of the vacuum may be necessary to prevent overflowing the container. Keep the mixture under a full vacuum for 5-10 minutes after the material has receded in the container.
7. Bleed air slowly into the vacuum chamber. When the chamber is at atmospheric equilibrium, remove the cover plate and take out the container.
8. Pour the desired material slowly in a steady stream from one end of the mold box so that the material flows evenly over the pattern. This will minimize the entrapment of air bubbles under the flowing rubber. A "print" coat may be poured first over the pattern, which will also reduce the possibility of entrapping air in the cured rubber. A mold release (petroleum jelly) may be applied on the pattern first to improve release if desired.
9. **CURING:**
 - A. **ROOM TEMPERATURE CURING SYSTEMS:** Allow the rubber to cure for 16-24 hours at 75°F (24°C) before removing the cured rubber from the pattern. For best results, allow the mold to air cure an additional 24 hours after the initial overnight cure before putting mold into production. Room temperature curing assures the lowest possible shrinkage. If cure acceleration is desired, mild heat may be employed. To minimize shrinkage, cure rubber at 100-130°F (38-54°C) for 4-6 hours. Higher temperatures may cause excessive shrinkage to occur.
 - B. **HEAT CURING SYSTEMS:** BLUESTAR SILICONES heat-curing systems are primarily used for roll and transfer print pad applications where long work life and pot life are needed. FOLLOW THE SUGGESTED PRODUCT CURE SCHEDULE GUIDE LISTED ON FRONT OF SPECIFIC PRODUCT INFORMATION SHEET.
10. For bonding to wood or metals, use **BLUESIL™ V-04 primer**. Follow recommendations on the **BLUESIL™ V-04** primer technical data sheet for best results.

MIXED PROCESSING PROPERTIES WILL BE AFFECTED BY TEMPERATURE VARIATIONS

- ◆ A decrease in work life and pot life may be expected to occur at temperatures exceeding 75°F (24°C). Room temperature curing moldmaking rubbers are particularly sensitive to higher temperatures. Refrigeration of the base (Part A) prior to use in hot environments has shown to improve the handling properties of these materials.
- ◆ Lower temperatures will increase the work life and pot life of this material. Cure temperatures below 68°F (20°C) are not recommended, and have been found to cause a reduction in final cure hardness and physical properties.
- ◆ This system contains a platinum catalyst, which may be inhibited by materials found in some organic polymer systems, chlorinated solvents, and some substrates. Especially troublesome materials are: amine cured epoxies, sulfur cured organic rubber systems such as natural rubber, polysulfide rubber, latex rubber and adhesives, sulfur containing modeling clays, PVC coated surfaces, and tin catalyzed silicone RTV rubbers. A patch test to determine compatibility is recommended when doubt exists.

Storage and shelf life

BLUESIL™ V-243 when stored in its original unopened packaging, at a temperature of 24°C (75°F), may be stored for 24 months from the date of manufacture. Beyond this date, Bluestar Silicones no longer guarantees that the product meets the sales specifications.

Safety

Please read the container labels for **BLUESIL™ V-243** or consult the Material Safety Data Sheet (MSDS) before handling for safe use, physical and health hazard information. The curing agent for this material can generate a flammable gas upon contact with acidic, basic, or oxidizing materials. The MSDS is not included with the product packaging, but can be obtained by contacting Bluestar Silicones at 866-474-6342 or consult your Bluestar Silicones representative.

Packaging

BLUESIL™ V-243 is available in 2 kg, 20 kg, and 200 kg containers.

BLUESIL™ is a Trademark of *Bluestar Silicones*

 EUROPE	 NORTH AMERICA	 LATIN AMERICA	 ASIA PACIFIC
<i>Bluestar Silicones France</i> 21 Avenue Georges Pompidou F69486 Lyon Cedex 03 FRANCE Tel. (33) 4 72 13 19 00 Fax (33) 4 72 13 19 88	<i>Bluestar Silicones USA</i> Two Tower Center Boulevard Suite 1601 East Brunswick, NJ 08816-1100 United States Tel. (1) 732 227 2060 Fax (1) 732 249 7000	<i>Bluestar Silicones Brazil Ltda.</i> Av. Maria Coelho Aguiar, 215 Bloco G - 1º Andar 05804-902 - São Paulo - SP - Brazil Tel. (55) 11 3747 7887 Fax (55) 11 3741 7718	<i>Bluestar Silicones Hong Kong</i> Trading Co. Ltd. 29 th Floor, 88 Hing Fat Street Causeway Bay Hong Kong Tel. (852) 3106 8200 Fax (852) 2979 0241

Warning to users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards to infringement of or prejudice to third party rights through the use of our products. **BLUESTAR SILICONES** warrants that its products comply with its sales specifications. This information must not be used as a substitute for necessary prior tests, which ensure that a product is suitable for a given use. Determination of the suitability of product for the uses and applications contemplated by user and others shall be the sole responsibility of user. Users are responsible for ensuring compliance with local legislation and for obtaining necessary certifications and authorizations. Users are requested to ensure that they are in possession of the latest version of this document; please contact **BLUESTAR SILICONES** for the latest version and any additional information.