

# DUNAPOX™ BLACK AD 135

Rev. N°1 - Date 01/16/2018

## Description

Two-component epoxy adhesive  
Designed to work at high temperatures  
Hardening at room temperature Medium/Slow  
Hardening in oven Medium  
Viscosity: Gel  
Sandable  
100% Reactive

## Typical Uses

Glueing of various materials.  
Sealing and priming of tooling/modeling boards. Primed surface can be sanded to obtain desired surface finishing.

## Suggested Materials

CORINTHO® boards  
CORAFOAM® boards  
Epoxy boards

## Typical characteristics - Resin

Component	Resin		
Name	DUNAPOX™ BLACK AD 135		
Density (25°C/77°F)	ASTM D891	lb/ft <sup>3</sup> (g/ml)	104.9-107.4 (1,68-1,72)
Viscosity (25°C/77°F)	ASTM D2196	P (mPa s)	Thixotropic
Storage temperature		°F (°C)	50-95 (10-35)
Shelf Life		Months	12
Appearance	Black Paste		

## Typical characteristics - Hardener

Component	Hardener		
Name	DUNAPOX™ H 156		
Density (25°C/77°F)	ASTM D891	lb/ft <sup>3</sup> (g/ml)	62.4-63.7 (1,00-1,02)
Viscosity (25°C/77°F)	ASTM D2196	P (mPa s)	0.6-0.9 (60-90)
Storage temperature		°F (°C)	50-95 (10-35)
Shelf Life		Months	12
Appearance	Yellowish transparent liquid		

## Mixing Ratio

Mixing ratio by weight RES/HAR	parts	100/20
--------------------------------	-------	--------

## Characteristics of the system

Colour	Black		
Density (25°C/77°F)		lb/ft <sup>3</sup> (g/ml)	104.9-107.4 (1,68-1,72)
Minimum application temperature		°F (°C)	+50 (+10)
Gel time (25°C/77°F)	film	h min' sec"	4h-5h
Gel time (60°C/140°F)	film	h min' sec"	45'-60'



Distributed By  
Freeman Manufacturing & Supply Co.  
www.freemansupply.com 800-321-8511



# DUNAPOX™ BLACK AD 135

Rev. N°1 - Date 01/16/2018

Handling time (25°C/77°F)	h min' sec''	12h-15h
Complete hardening	days	10-15
Suggested thickness	In (mm)	0.007 (0.2)
Coverage rate	lb/ft <sup>2</sup> (g/m <sup>2</sup> )	0.040-0,061 (200-300)
Operating temperature	°F (°C)	Max. +400 (+205)

## Mixing

Strictly observe the mixing ratio; any variation may seriously compromise the characteristics of the final product. Avoid excessive turbulence during mixing, with consequent undesirable inclusions of air.

It is possible to mix/distribute by hand with a spatula, trowel, notched trowel, brush, roller or spray.

## Storage

Wherever possible apply products in ventilated areas, wearing gloves, protective eyewear, barrier creams and suitable protective clothes. Avoid contact with unhardened materials.

In case of accidental contact with the ski, wash yourself with lukewarm water and soap for at least 10 minutes. Do not wash affected areas with solvents as this may increase contamination.

Lifetime of products is referred to materials stored in sealed containers in dry rooms, at recommended temperatures and protected from direct sunlight.

Expiry is printed on packaging

Moisture and/or storage in humid conditions may affect the characteristics of the components.

## Remarks

For usage information, personal protective equipment, transport, storage and disposal of waste it is essential to refer to the Material Safety Data Sheets.

Values shown are determined from laboratory tests and obtained under controlled conditions; they outline typical characteristics and they do not constitute anyhow a sales specification; they are based on DUNA-USA Inc.'s current knowledge and experience of the products when properly stored, handled and applied in accordance with our recommendations.

This technical Data Sheet cancels and replaces any other previous issue.

DUNA-USA Inc. does not accept any responsibility for incorrect use of its products as it cannot ensure the correct methods of application have been followed; we therefore specifically disclaim any liability for consequential or incidental damages of any kind, including lost profits.

DUNA-USA Inc reserves the right to change the data in this information sheet without any prior notice.