






FUMED METAL OXIDES

CAB-O-SIL® TS-720 FUMED SILICA

Product highlights

CAB-O-SIL TS-720 fumed silica is a medium surface area fumed silica which has been surface treated with polydimethylsiloxane (PDMS). This surface treatment results in a hydrophobic silica with a very different performance than untreated silica.



- High purity
- Aggregated structure
- ♦ Submicron particle size
- Low bulk density
- Hydrophobic surface chemistry



Key applications

CAB-O-SIL TS-720 fumed silica is used for rheology control in a wide variety of adhesives, composite and coatings applications.

This product provides the following performance advantages in medium to high polarity systems:

- Thickening efficiency
- Sag resistance or high film build
- Anti-settling of pigments and fillers
- Shear-thinning rheological behavior
- Stable rheological performance over time

Epoxy Adhesives and Coatings

In epoxy adhesives and coatings, CAB-O-SIL TS-720 fumed silica provides good thickening efficiency, sag resistance (or film build) and anti-settling of pigments and fillers.

Polyurethane Adhesives and Coatings

In polyurethane adhesives and coatings, CAB-O-SIL TS-720 fumed silica provides the same efficient, stable rheology control as in epoxy systems. In addition, the hydrophobic surface of CAB-O-SIL TS-720 fumed silica introduces very little moisture into these systems, retarding premature cross-linking of moisture cured systems.

Vinyl Ester Laminating Resins and Gel Coats

While untreated silicas are effective thickeners of unsaturated polyester resins, CAB-O-SIL TS-720 fumed silica is a more efficient, stable rheology control additive for higher polarity systems like vinyl ester laminating resins and gel coats.

CAB-O-SIL® TS-720 FUMED SILICA



Product form and logistics

- Product form: powder
- Regional availability: global
- Packaging options:
 - 18 X 10 kg (net weight 180 kg) shrink-wrapped pallets
 - 18 x 10 lb (net weight 180 lbs) poly shrouded units
 - 150 kg FIBCs

For information on product-specific storage conditions, please refer to the applicable Safety Data Sheet (SDS) available from your Cabot representative or at cabotcorp.com.

The CAB-O-SIL name is registered trademark of Cabot Corporation.

NORTH AMERICA

Business & Technology Center 157 Concord Road Billerica, MA 01821-7001 United States

T+1 800 462 2313 F +1 978 670 7035

SOUTH AMERICA

F +55 11 3253 0051

Cabot Brasil Industria e Comercio Ltda. Rua do Paraíso 148 - 5° andar 04103-000 São Paulo Brazil T +55 11 2144 6400

FUROPE

SIA Cabot Latvia 101 Mukusalas Street LV-1004 Riga Latvia T+371 670 50 900 F+371 670 50 985

MIDDLE EAST/AFRICA

Cabot Specialty Chemicals Jebel Ali Free Zone LOB 15, Office 424, Dubai United Arab Emirates T+971 4 8871 800 F +971 4 8871 801

ASIA PACIFIC

Cabot China Ltd. 558 Shuangbai Road Minghang District Shanghai 201108 China T +86 21 5175 8800

F +86 21 6434 5532

Cabot Specialty Chemicals, Inc. Sumitomo Chiba-Daimon Bldg, 3F 2-5-5 Shiba Daimon, Minato-ku, Tokyo 105-0012 Japan T +81 6820 0255 F +81 3 5425 4500

The data and conclusions contained herein are based on work believed to be reliable, however, Cabot cannot and does not guarantee that similar results and/or conclusions will be obtained by others. This information is provided as a convenience and for informational purposes only. No guarantee or warranty as to this information, or any product to which it relates, is given or implied. This information may contain inaccuracies, errors or omissions and CABOT DISCLAIMS ALL WARRANTIES EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE AS TO (i) SUCH INFORMATION, (ii) ANY PRODUCT OR (iii) INTELLECTYAL PROPERTY INFRINGEMENT. In no event is Cabot responsible for, and Cabot does not accept and hereby disclaims liability for, any damages whatsoever in connection with the use of or reliance on this information or any product to which it relates.

