

MATERIAL SAFETY DATA SHEET

1. IDENTIFICATION OF THE SUBSTANCE/PREPARATION AND THE COMPANY/UNDERTAKING

Telephone numbers:	(517) 546-4520
Manufacturer/Supplier:	CHEM-TREND LIMITED PARTNERSHIP P.O. BOX 860 HOWELL, MI 48844-0860
Product Name:	CHEMLEASE PMR

2. HAZARDS IDENTIFICATION

Physical State:	Liquid
Appearance:	Liquid
Color:	Clear
Odor:	Solvent
Emergency Overview:	DANGER: FLAMMABLE! Vapors may travel to a source and flash back.
Principle routes of exposure:	Skin, eyes, respiratory tract, gastrointestinal tract
See Toxicological Information (section 11)	

3. COMPOSITION/INFORMATION ON INGREDIENTS

Ingredient	CAS Registry Number	Weight %
o-Xylene	95-47-6	50 - 60%
Aromatic petroleum distillates	64742-95-6	20 - 30%
1,2,4-Trimethylbenzene	95-63-6	10 - 20%
1,3,5-Trimethylbenzene	108-67-8	1 - 5%
Diethylbenzene	25340-17-4	1 - 5%
Isopropylbenzene	98-82-8	1 - 5%
Resin blend	Proprietary	1 - 5%

Revision number: 0

Page 1 of 8

Chemlease®, Hydrolease®, Lusin®, Mono-Coat®, Mono-Lube®, Perma-Mold®, Power-Lube®, Pura®, RDP®, RPM®, Safety-Lube® are registered trademarks of Chem-Trend Limited Partnership

CHEMLEASE PMR

4. FIRST AID MEASURES

Skin contact:	Wash off immediately with soap and plenty of water, removing all contaminated clothes and shoes.
Eye contact:	Rinse thoroughly with plenty of water for at least 15 minutes and contact a physician.
Inhalation:	Inhalation of high vapour concentrations may cause symptoms like headache, dizziness, tiredness, nausea and vomiting. Move to fresh air. If symptoms persist, call a physician.
Ingestion:	Do not induce vomiting: contains petroleum distillates and/or aromatic solvents. Aspiration may cause pulmonary oedema and pneumonitis. Contact a physician immediately.
Aggravated Medical Conditions:	Respiratory, liver, and kidney.
Notes to physician:	No information available.

5. FIRE-FIGHTING MEASURES

Flash point:	85 °F , 29°C (Pensky-Martens, ASTM D 93, ISO 1523, DIN 51 755)
Flame extension test, inches (aerosol products only):	Not applicable or no information available.
Suitable extinguishing media:	Carbon dioxide (CO2). Dry chemical. Foam. Do not use a direct stream of water..
Unusual hazards:	Flammable.
Special protective equipment for firefighters:	As in any fire, wear self-contained breathing apparatus pressure-demand, MSHA/NIOSH (approved or equivalent) and full protective gear.
Specific methods:	Standard procedure for chemical fires. Cool containers / tanks with spray water
Explosive properties:	No information available.

6. ACCIDENTAL RELEASE MEASURES

Method(s) for cleanup:	
Small spills:	Take precautionary measures against static discharges. Soak up with inert absorbent material and dispose of as hazardous waste.
Large spills:	Dam up. Take precautionary measures against static discharges. Take up mechanically and collect in suitable container for disposal.

7. HANDLING AND STORAGE

Handling:	
Technical measures/precautions:	Ensure adequate ventilation. Take precautionary measures against static discharges.

Revision number: 0

Page 2 of 8

Chemlease®, Hydrolease®, Lusin®, Mono-Coat®, Mono-Lube®, Perma-Mold®, Power-Lube®, Pura®, RDP®, RPM®, Safety-Lube® are registered trademarks of Chem-Trend Limited Partnership

CHEMLEASE PMR

7. HANDLING AND STORAGE

Safe handling advice:	Handle in accordance with good industrial hygiene and safety practice. Normal measures of preventive fire protection. Take precautionary measures against static discharges. Keep product and empty container away from heat, open flames, and other sources of ignition. Bond and ground containers during transfer of material. Do not puncture empty containers. Do not re-use empty containers for other materials.
Storage:	
Technical measures/storage conditions:	Keep containers tightly closed in a dry, cool and well-ventilated place. Keep product and empty container away from open flames, hot surfaces and sources of ignition. Store at temperatures not exceeding 110°F.
Incompatible products:	Strong oxidizing agents.
Other precautions:	None

8. EXPOSURE CONTROLS / PERSONAL PROTECTION

Ingredient	CAS Registry Number	ACGIH TWA:	OSHA - TWA:	OSHA - Skin Notations	OSHA Z3 Mineral Dusts
o-Xylene	95-47-6	100 ppm 150 ppm	-	-	-
Aromatic petroleum distillates	64742-95-6	-	-	-	-
1,2,4-Trimethylbenzene	95-63-6	25 ppm	-	-	-
1,3,5-Trimethylbenzene	108-67-8	25 ppm	-	-	-
Diethylbenzene	25340-17-4	-	-	-	-
Isopropylbenzene	98-82-8	50 ppm	=50ppmTWA =245mg/m ³ TWA	-	-
Resin blend	Proprietary	-	-	-	-

Engineering measures to reduce exposure: Ensure adequate ventilation. Where reasonably practicable this should be achieved by the use of local exhaust ventilation and good general extraction.

Personal Protective Equipment

Respiratory protection:	In case of insufficient ventilation wear suitable respiratory equipment.
Hand protection:	Impervious gloves
Eye protection:	Tightly-fitting safety goggles or safety glasses with side shields.
Skin and body protection:	Lightweight protective clothing. Usual safety precautions while handling the product will provide adequate protection against this potential effect.

9. PHYSICAL AND CHEMICAL PROPERTIES

Revision number: 0

Page 3 of 8

Chemlease®, Hydrolease®, Lusin®, Mono-Coat®, Mono-Lube®, Perma-Mold®, Power-Lube®, Pura®, RDP®, RPM®, Safety-Lube® are registered trademarks of Chem-Trend Limited Partnership

CHEMLEASE PMR

Initial boiling point:	284 °F , 140 °C
Specific gravity:	0.87
Bulk density (lb/gal):	7.26
Vapor pressure in mm Hg at 20 °C (68 °F):	No information available.
Vapor density (air = 1):	>1
Evaporation rate:	<1 (n-butyl acetate = 1)
Volatiles content (%):	90 - 100%
Solubility in water:	Insoluble
pH of concentrate:	Not applicable.
Melting point/range:	Not applicable
Flash point:	85 °F , 29°C (Pensky-Martens, ASTM D 93, ISO 1523, DIN 51 755)
Flammability limits in air:	Percent by volume

Ingredient	CAS Registry Number	Lower (%):	Upper (%):
o-Xylene	95-47-6	1.0	7.0
Aromatic petroleum distillates	64742-95-6	1.0	7.0
1,2,4-Trimethylbenzene	95-63-6	0.9	6.4
1,3,5-Trimethylbenzene	108-67-8	No information available	No information available
Diethylbenzene	25340-17-4	1.1	6.2
Isopropylbenzene	98-82-8	0.9	6.5

10. STABILITY AND REACTIVITY

Stability:	Stable.
Conditions to avoid:	Keep away from open flames, hot surfaces and sources of ignition.
Materials to avoid:	Strong oxidising agents.
Hazardous decomposition products:	Carbon oxides. Formaldehyde may be evolved at elevated temperatures.
Polymerization:	Hazardous polymerisation does not occur.

Revision number: 0

Page 4 of 8

Chemlease®, Hydrolease®, Lusin®, Mono-Coat®, Mono-Lube®, Perma-Mold®, Power-Lube®, Pura®, RDP®, RPM®, Safety-Lube® are registered trademarks of Chem-Trend Limited Partnership



11. TOXICOLOGICAL INFORMATION

Acute toxicity

Component Information:

Ingredient	CAS Registry Number	LD50 Oral	LD50 Dermal	LC50 Inhalation
o-Xylene	95-47-6	3609 mg/kg (Rat)	-	2180 ppm (Rat) 4 h
Aromatic petroleum distillates	64742-95-6	8400 mg/kg (Rat)	2000 mg/kg (Rabbit)	3400 ppm (Rat) 4 h 5.2 mg/L (Rat) 4 h
1,2,4-Trimethylbenzene	95-63-6	3400 mg/kg (Rat)	3160 mg/kg (Rabbit)	18 g/m ³ (Rat) 4 h
1,3,5-Trimethylbenzene	108-67-8	5000 mg/kg (Rat)	-	24 g/m ³ (Rat) 4 h
Diethylbenzene	25340-17-4	-	-	-
Isopropylbenzene	98-82-8	1400 mg/kg (Rat)	3160 mg/kg (Rabbit)	39000 mg/m ³ (Rat) 4 h
Resin blend	Proprietary	-	-	-

Acute effects

Product contains proprietary ingredients. Health hazards are listed below.

Skin contact:

Prolonged contact may defat skin, causing irritation and/or dermatitis.

Eye contact:

May cause eye irritation.

Inhalation:

High levels above the TLV cause stupor, headache, nausea, dizziness, unconsciousness, and may produce adverse effects on vision.

Ingestion:

Ingestion may cause gastrointestinal irritation, nausea, vomiting and diarrhea. Material entering lungs during swallowing or vomiting causes lung inflammation and other lung injury.

Sensitization:

No information available.

Other effects:

No information available.

Chronic effects

Carcinogenic effects:

Ingredient	CAS Registry Number	NTP:	IARC:	OSHA:
o-Xylene	95-47-6	No	No	No
Aromatic petroleum distillates	64742-95-6	No	No	No
1,2,4-Trimethylbenzene	95-63-6	No	No	No
1,3,5-Trimethylbenzene	108-67-8	No	No	No
Diethylbenzene	25340-17-4	No	No	No
Isopropylbenzene	98-82-8	No	No	No
Resin blend	Proprietary	No	No	No

Mutagenic effects:

No information available.

Reproductive toxicity:

No information available.

Revision number: 0

Page 5 of 8

Chemlease®, Hydrolease®, Lusin®, Mono-Coat®, Mono-Lube®, Perma-Mold®, Power-Lube®, Pura®, RDP®, RPM®, Safety-Lube® are registered trademarks of Chem-Trend Limited Partnership

CHEMLEASE PMR

11. TOXICOLOGICAL INFORMATION

Target organ effects: No information available.

12. ECOLOGICAL INFORMATION

Ecotoxicity: No data available.

13. DISPOSAL CONSIDERATIONS

Method(s) of disposal: Dispose of in accordance with local, state, and federal regulations.

US EPA Waste code(s): D001 because of its ignitability if the product is disposed of in its original form.

14. TRANSPORTATION INFORMATION

IMDG - Marine Pollutants This product does not contain marine pollutants as classified by the International Maritime Organization.

Emergency Response Guidebook 128 (ERG) No:

DOT

UN/NA ID No: UN1866
Proper shipping name: Resin solution
Hazard Class: 3
Packing group: III

ICAO/IATA

UN ID No: UN1866
Proper shipping name: Resin solution
Hazard Class: 3
Packing group: III

IMDG/IMO

UN ID no: UN1866
Proper shipping name: Resin solution
Hazard class: 3
Packing group: III

15. REGULATORY INFORMATION

U.S. Regulations

OSHA Hazardous Chemical: Yes

Sara Title III

CERCLA/SARA (304) Hazardous Substances and RQs

Ingredient	CAS Registry Number	Weight %	RQ
------------	---------------------	----------	----

Revision number: 0

Page 6 of 8

Chemlease®, Hydrolease®, Lusin®, Mono-Coat®, Mono-Lube®, Perma-Mold®, Power-Lube®, Pura®, RDP®, RPM®, Safety-Lube® are registered trademarks of Chem-Trend Limited Partnership



15. REGULATORY INFORMATION

o-Xylene	95-47-6	50 - 60%	100 lb 1000 lb
Aromatic petroleum distillates	64742-95-6	20 - 30%	-
1,2,4-Trimethylbenzene	95-63-6	10 - 20%	-
1,3,5-Trimethylbenzene	108-67-8	1 - 5%	-
Diethylbenzene	25340-17-4	1 - 5%	-
Isopropylbenzene	98-82-8	1 - 5%	5000 lb
Resin blend	Proprietary	1 - 5%	-

SARA (302) Extremely Hazardous Substances and RQs

Ingredient	CAS Registry Number	Weight %	RQs
o-Xylene	95-47-6	50 - 60%	-
Aromatic petroleum distillates	64742-95-6	20 - 30%	-
1,2,4-Trimethylbenzene	95-63-6	10 - 20%	-
1,3,5-Trimethylbenzene	108-67-8	1 - 5%	-
Diethylbenzene	25340-17-4	1 - 5%	-
Isopropylbenzene	98-82-8	1 - 5%	-
Resin blend	Proprietary	1 - 5%	-

None present or none present in regulated quantities.

SARA (311/312) Classification:

Acute health hazard: Yes

Chronic health hazard: No

Fire: Yes

Sudden release of pressure: No

Reactive: No

SARA (313) Toxic Chemicals

Ingredient	CAS Registry Number	Weight %	SARA (313) List
o-Xylene	95-47-6	50 - 60%	X
Aromatic petroleum distillates	64742-95-6	20 - 30%	Not Listed
1,2,4-Trimethylbenzene	95-63-6	10 - 20%	X
1,3,5-Trimethylbenzene	108-67-8	1 - 5%	Not Listed
Diethylbenzene	25340-17-4	1 - 5%	Not Listed
Isopropylbenzene	98-82-8	1 - 5%	X
Resin blend	Proprietary	1 - 5%	Not Listed

International Inventories

Australia:	All the constituents of this material are listed on the Australian Inventory of Chemical Substances (AICS).
Canada:	This product complies with NDSL
China:	This product complies with CLECS.

Revision number: 0

Page 7 of 8

Chemlease®, Hydrolease®, Lusin®, Mono-Coat®, Mono-Lube®, Perma-Mold®, Power-Lube®, Pura®, RDP®, RPM®, Safety-Lube® are registered trademarks of Chem-Trend Limited Partnership



CHEMLEASE PMR

15. REGULATORY INFORMATION

Europe:	This product complies with EINECS
Japan:	This product complies with ENCS/MITI.
Korea:	This product does not comply with ECL.
New Zealand:	This product does not comply with NEWZ
Philippines:	This product complies with PICCS.
United States:	This product complies with TSCA.

16. OTHER INFORMATION

Hazardous Material Information System (USA):

Health: 1 **Flammability:** 3 **Physical hazard:** 0 **Personal Protection code:** H

National Fire Protection Association (USA):

Health: 1 **Flammability:** 3 **Instability:** 0 **Special Hazards:** None

All revisions are marked with one or more asterisks (*)

Prepared by: Karen M. Kuroda

Revision number: 0

Revision date: 03/06/2008

Review date: 04/14/2008

Print date: 04/14/2008

Disclaimer

Information presented herein has been compiled from information provided to us by our suppliers and other sources considered to be dependable and is accurate and reliable to the best of our knowledge and belief but is not guaranteed to be so. Nothing herein is to be construed as recommending any practice or the use of any product in violation of any patent or in violation of any law or regulation. It is the users' responsibility to determine the suitability of any material for a specific purpose and to adopt such safety precautions as may be necessary. We make no warranty as to the results to be obtained in using any material and, since conditions of use are not under our control, we must necessarily disclaim all liability with respect to the use of any material supplied by us.

Revision number: 0

Page 8 of 8

Chemlease®, Hydrolease®, Lusin®, Mono-Coat®, Mono-Lube®, Perma-Mold®, Power-Lube®, Pura®, RDP®, RPM®, Safety-Lube® are registered trademarks of Chem-Trend Limited Partnership

