

# ARALDITE® 2019 Structural Adhesive

## Product Description

ARALDITE® 2019 structural adhesive is a two-component, epoxy adhesive paste of high strength and toughness. Performances can be enhanced by post-curing at elevated temperature. It has been designed to perfectly bond onto composites, especially CFRP, but it is suitable for bonding a wide variety of metals, ceramics and many other substrates in common use.

## Features

- Very high lap shear
- Bonds a wide variety of materials (metal, composite and thermoplastics)
- Temperature resistant up to 284°F (140°C)
- Extremely tough and resilient adhesive
- Contains spacers to ensure a minimum bond line thickness of 0.05 mm

## Typical Properties\*

Property	Component A	Component B	ARALDITE® 2019
Appearance – Visual (A112)	Black paste	Yellowish paste	Black paste
Density, g/cm <sup>3</sup>	1.2	1.0	~1.1
Viscosity at 77°F (25°C), cP (A191)	80,000-100,000	10,000-15,000	Thixotropic
Pot life at 77°F (25°C), 100 g, min	--	--	100-120
Lap shear strength at 23°C, MPa (A501)	--	--	> 25

\* Specified data are on a regular basis analyzed. Data which is described in this document as 'typical' is not analyzed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

## Processing

### Pretreatment

The strength and durability of a bonded joint are dependent on proper treatment of the surfaces to be bonded. At the very least, joint surfaces should be cleaned with a good degreasing agent such as acetone, isopropanol (for plastics) or other proprietary degreasing agents in order to remove all traces of oil, grease and dirt. Low grade alcohol, gasoline (petrol) or paint thinners should never be used. The strongest and most durable joints are obtained by either mechanically abrading or chemically etching (“pickling”) the degreased surfaces. Abrading should be followed by a second degreasing treatment

### Mix Ratio

Product	Parts by weight	Parts by volume
Component A	100	100
Component B	43	50

The resin and hardener should be blended until they form a homogeneous mix. ARALDITE® 2019 is available in cartridges incorporating mixers and can be applied as ready to use adhesive with the aid of the tool recommended by Huntsman Advanced Materials

### Application of adhesive

The resin/hardener mix is applied with a spatula, to the pretreated and dry joint surfaces. A layer of adhesive 0.05 to 0.10 mm thick will normally impart the greatest lap shear strength to the joint. If possible, the adhesive should be applied on both substrates and the joint components must be assembled and clamped as soon as the adhesive has been applied. For bond line thicknesses below 0.5 mm, the components must be assembled within 60 minutes after the application of the adhesive, for higher bond line thicknesses the components must be assembled within 30 minutes after application of the adhesive. An even contact pressure throughout the joint area will ensure optimum cure.

### Mechanical Processing

Specialist firms have developed metering, mixing and spreading equipment that enables the bulk processing of adhesive. We will be pleased to advise customers on the choice of equipment for their particular needs.

### Equipment Maintenance

All tools should be cleaned before adhesive residue has had time to cure. The removal of cured residue is a difficult and time-consuming operation. If solvents such as acetone are used for cleaning, operatives should take the appropriate precautions and, in addition, avoid skin and eye contact.

### Cure times to reach minimum shear strength

Temperature, °F (°C)		73 (23)	104 (40)	140 (60)	212 (100)
Cure time to reach LSS* > 145 psi (1 MPa)	hr	4.5	-	-	-
	min	-	100	20	<5
Cure time to reach LSS > 1450 psi (10 MPa)	hr	6	2	-	-
	min	-	-	30	10

LSS = Lap shear strength

### Curing requirements

To achieve optimum performance properties an elevated temperature cure or post cure is recommended. This adhesive will solidify to a hand able state but will not fully cure at temperatures below 140°F (60°C). Suggested cure schedules in order to improve the heat resistance of the adhesive are the following:


- 16 hours at 104F (40°C) + 1 hour at 176F (80°C)
- 3 hours at 176°F (80°C)
- 1 hour at 266°F (130°C)
- 30 min at 302°F (150°C)

### Typical Physical Properties


Unless otherwise stated, the figures given below were all determined by testing standard specimens made by lap-jointing 114 x 25 x 1.6 mm strips of aluminum alloy. The overlap was 12.5 x 25 mm in each case. The figures were determined with typical production batches using standard testing methods and are provided solely as technical information and do not constitute a product specification.

#### Average lap shear strengths of typical metal-to-metal joints (ISO 4587) (typical average values)


Cured for 16 hours at 104°F (40°C) + 1 hour at 176°F (80°C) and tested at 73°F (23°C). Pretreatment - Sandblasting and alcohol degreasing.



Other cure cycles, on aluminum and tested at 73°F (23°C). Pretreatment: sandblasted and degreased.



**Average lap shear strengths of typical plastic-to-plastic joints (ISO 4587) (typical average values)** Cured for 16 hours at 104°F (40°C) + 1 hour at 176°F (80°C) and tested at 73°F (23°C). Pretreatment - Lightly abraded and alcohol degreased.




\* substrate failure or substrate delamination

### Lap shear strength versus temperature (ISO 4587) (typical average values)


Cure: 16 hours at 104°F (40°C) + 1 hour at 176°F (80°C).

Substrate: Aluminium sandblasted and degreased.




### Lap shear strength versus immersion in various media (typical average values)

Unless otherwise stated, L.S.S. was determined after immersion for 30, 60 and 90 days at 73°F (23°C).  
 Cure: 16 hours at 104°F (40°C) + 1 hour at 176°F (80°C).  
 Substrate: Aluminum, sandblasted and degreased.



### Lap shear strength versus heat ageing (ISO 4587) (typical average values)


Cure: 16 hours at 104°F (40°C) + 1 hour at 176°F (80°C) and tested at 73°F (23°C).  
Substrate: Aluminum sandblasted and degreased.



\*25 cycles: -30°C to + 70°C

### Lap shear strength versus tropical weathering (typical average values)

Conditions: 40°C / 92% RH  
Substrate: Aluminum  
Cured for 16 hours at 104°F (40°C) and tested at (23°C)  
Pretreatment - Sand blasting



### Mechanical Properties (Typical values)

Property		Cure Schedule	Value
Tg (DSC), °F (°C)	ISO 11357-2	16 hours at 40°C	140 (60)
		16 hours at 40°C + 1 hour at 80°C	178 (81)
		3 hours at 80°C	194 (90)
		1 hour at 130°C	(216) 102
		0.5 hour / 150°C	210 (99)
		24 hours at RT + 2 hours at 150°C	252 (122)
Roller peel test (sandblasted aluminum), lbf-in (N/mm)	ISO 4578	16 hours at 40°C	34-46 (6-8)
		16 hours at 40°C + 4 hours at 80°C	5.7-17 (1-3)
Tensile strength at 23°C, ksi (MPa)	ISO 527	16 hours at 40°C + 1 hour at 80°C	5.8 (40)
E-modulus, ksi (MPa)		16 hours at 40°C + 1 hour at 80°C	232 (1,600)
Elongation at break, %		16 hours at 40°C + 1 hour at 80°C	4.3
Flexural strength at 23°C, ksi (MPa)	ISO 178	16 hours at 40°C + 1 hour at 80°C	9.4 (65)
Flexural modulus, ksi (MPa)		16 hours at 40°C + 1 hour at 80°C	218 (1,500)
Durometer Hardness (Shore D) at 23°C	ISO 868/03	16 hours at 40°C + 1 hour at 80°C	75
Bend notch test tested at 23°C/50%RH K <sub>1c</sub> , MPa.m <sup>1/2</sup> G <sub>1c</sub> , kJ.m <sup>-2</sup>	ISO 13586	16 hours at 40°C + 1 hour at 80°C	1.7
			1.9
Shear modulus G', ksi (MPa), at -40°C 0°C 23°C 60°C 90°C 140°C	ISO 6721	--	189 (1,300)
			133 (920)
			116 (800)
			71 (490)
			8.7 (60)
			0.17 (1.2)



## Storage

**ARALDITE® 2019 structural adhesive** should be stored in a dry place, in the original sealed containers, at temperatures between 2°C and 40°C (36°F and 104°F). Under these storage conditions, the product has a shelf life of **3 years** (from date of manufacture). The expiry date is indicated on the label. The product should not be exposed to direct sunlight.

If stored below 60°F, the adhesive should be brought to 60°F - 77°F and conditioned at this temperature for some time prior to use.

## Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

### First Aid!

Refer to SDS as mentioned above.

**KEEP OUT OF REACH OF CHILDREN**

**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

## Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

# Advanced Materials

## Technical Datasheet

 DISTRIBUTED BY  
Freeman Mfg. & Supply Co.  
www.FreemanSupply.com

**HUNTSMAN**  
Enriching lives through innovation

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

**ARALDITE®** is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all countries.

© 2020 Huntsman Advanced Materials Inc.

### Main Offices:

#### **Huntsman Corporation**

10003 Woodloch Forest Dr  
The Woodlands, TX 77380  
888-564-9318

#### **Huntsman Advanced Technology Center**

8600 Gosling Rd.  
The Woodlands, TX 77381  
281-719-7400