

Advanced Materials**Araldite® LY 8605 / Aradur® 8605 System**

EPOXY RESIN SYSTEM

DESCRIPTION :

Araldite® LY 8605 (Resin) / Aradur® 8605 (Hardener) is a two-component, low-viscosity epoxy system developed for use in the production of advanced composites using vacuum-assisted resin transfer molding (VARTM), resin transfer molding (RTM), Seemans Composite Resin Injection Molding Process (SCRIMPSM), or other infusion processes. The low-mixed viscosity and wet-out potential of Araldite® LY 8605 / Aradur® 8605 enhance processability parameters.

Araldite® LY 8605 / Aradur® 8605 has intermediate to high temperature performance. Composites produced with this product can achieve a glass transition of 300 °F (149 °C) following a post cure.

MIX RATIO :

By weight: 100 to 35 Resin to Hardener

Mixing Instructions : Measure each component accurately (\pm 5%) into clean containers. Thoroughly mix resin and hardener together (minimum 2 minutes) scraping container sidewalls, bottom and mixing stick several times to assure a uniform mix.

TYPICAL HANDLING PROPERTIES :

Tested @ 77 °F (25 °C) unless otherwise noted.

Property	Criteria	ASTM Test Method	Test Value
Color	Mixed		Transparent
Specific Gravity	Resin	D-792	1.10
	Hardener		0.94
Viscosity, cP	Resin	D-2393	1,200
	Hardener		100
	Mixed		700
Gel Time, minutes	100 gram mass	D-2471	480 - 580

NOTE : Typical Properties – These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed establishing product specifications, please consult with our Quality Control Department.

RECOMMENDED CURE SCHEDULE :

24 hours @ 77 °F (25 °C) plus 2 hours @ 250 °F (121 °C) plus 3 hours at 350 °F (177 °C), unless noted otherwise.

Please note that other cure schedules may be used to obtain comparable physical properties. Please contact RenShape Solutions' Technical Information Hotline (800) 759-7165 to discuss your application.

NEAT SYSTEM**TYPICAL CURED PROPERTIES :**

Cured 24 hours @ 77 °F (25 °C) plus 2 hours @ 250 °F (121 °C) plus 3 hours @ 350 °F (177 °C). Tested @ 77 °F (25 °C) unless otherwise noted.

Property	ASTM Test Method	Test Values
Specific Gravity	D-792	1.06
Cubic Inch per Pound		26
Hardness (Shore D)	D-2240	89
Ultimate Flexural Strength	D-790	12,200
Ultimate Flexural Modulu	D-790	380,000
Ultimate Tensile Strength, psi	D-638	6,921
Tensile Modulus, psi		366,555
% Elongation		2.5
Tg by DMA, E' onset, dry, °F (°C)	D-4065	307 (153)
Tg by DMA, E' onset, wet, °F (°C)	D-4065	270 (132)

NOTE : All properties are of neat product form (non-composite)

LAMINATE SYSTEM**TYPICAL CURED PROPERTIES :**

Tested @ 77 °F (25 °C) unless otherwise noted.

Property	ASTM Test Method	Test Values⁽¹⁾	Test Values⁽²⁾
Hardness (Shore D)	D-2240	89	--
Ultimate Flexural Strength, psi	D-790	34,520	59,425
Flexural Modulus, psi	D-790	0.879 x 10 ⁶	2.26 x 10 ⁶
Ultimate Tensile Strength, psi	D-638	48,133	--
Tensile Modulus, psi		2.50 x 10 ⁶	--
Tg by DMA, E' onset, dry, °F (°C)	D-4065	301 (150)	317 (159)
Ultimate Compressive Strength, psi	D-695	36,575	--
Compressive Modulus, psi		2.87 x 10 ⁶	--
Coefficient of Thermal Expansion	D-3386		
In/in/°F -22 to 86 °F (-30° to 30 °C)		7.5 x 10 ⁻⁶	--
In/in/°F 77° to 212 °F (25° to 100 °C)		7.2 x 10 ⁻⁶	--

LAY-UP PROCESS :

Panel Type : Approximately. 3 ft. x 2 ft. flat panel
Cloth Type : 8 layers, 1581 glass cloth
Cloth Rotation : 0,90 degree
Procedure : Vacuum bagged, flat panel
Laminate Resin Contact : 32.3 %

⁽¹⁾ Cured 24 hours at 77 °F (25 °C) plus 1 hour at 176 °F (80 °C) plus 8 hours at 284 °F (140 °C).

⁽²⁾ Cured 24 hours at 77 °F (25 °C) plus 1 hour at 176 °F (80 °C) plus 2 hours at 250 °F (121 °C) plus 2 hours at 300 °F (149 °C) plus 2 hours at 351 °F (177 °C).

PACKAGING :

<u>Unit</u>		<u>Weight</u>
5 gallon	<i>Resin</i>	40 lb.
5 gallon	<i>Hardener</i>	31.5 lb.
2 x gallon package	<i>Hardener</i>	14 lb.
Drum	<i>Resin</i>	450 lb.
Drum	<i>Hardener</i>	315 lb.

CONDITIONING :

Stir well before use. This material will separate.

HANDLING :

Work in a well ventilated area and use clean, dry tools for mixing and applying For two component system, combine the resin and hardener according to mix ratio. Mix together thoroughly and use immediately after mixing. Material temperature should not be below 18 °C (65 °F) when mixing.

STORAGE :

Araldite® LY 8605 (Resin) / Aradur® 8605 (Hardener) should be stored in a dry place, in the sealed original container, at temperatures between +2°C and +40°C (+35.6°F and +104°F). Under these storage conditions, the shelf life is 2 years. The product should not be exposed to direct sunlight.

PRECAUTIONARY STATEMENT :

Huntsman Advanced Materials Americas LLC maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to MSDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

IMPORTANT LEGAL NOTICE

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

WHILE ALL THE INFORMATION AND RECOMMENDATIONS IN THIS PUBLICATION ARE, TO THE BEST OF HUNTSMAN ADVANCED MATERIAL'S KNOWLEDGE, INFORMATION AND BELIEF, ACCURATE AT THE DATE OF PUBLICATION, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behavior of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behavior of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behavior should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

Ren, RenShape and RenInfusion are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2007 Huntsman Corporation or an affiliate thereof. All rights reserved.

Main Offices :

Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

**Huntsman Advanced Technology
Center**

8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400

Website :

www.huntsman.com/advanced_materials