



Become a member!

HUNTSMAN

Enriching lives through innovation

Advanced Materials

RenShape® 5008

HIGH PERFORMANCE, INTERMEDIATE TEMPERATURE EPOXY BOARD

DESCRIPTION :

RenShape® 5008 board is an epoxy material that is designed for use at temperatures up to 230°F (110°C). The board is well suited for building aerospace master models, lay-up tools for low and medium-temperature curing prepregs, and other heat-resistant tooling. RenShape® 5008 board features a low coefficient of thermal expansion to produce models and tools with good accuracy and dimensional stability. Among the key benefits of RenShape® 5008 board are:

ADVANTAGES	
	• Easy to CNC machine
	• Good edge definition
	• Good dimensional stability
	• Good surface finish
	• Prepreg compatible

ACCESSORIES

Matched Epoxy Adhesive
Ren-Weld® 5008 Adhesive

TYPICAL PROPERTIES*	Test Method	Test Values
Color	Visual	Light Blue
Density, lb./ft. ³ (g/cm ³)	ASTM D-792	42 (0.67)
Hardness, Shore D	ASTM D-2240	68
Ultimate Flexural Strength, psi (MPa)	ASTM D-790	4,600
Flexural Modulus, psi (MPa)	ASTM D-790	350,000
Ultimate Tensile Strength, psi (MPa)	ASTM D-638	3,500
Tg by DMA, E', °F (°C)	ASTM D-4065	231 (111)
Tg by DMA, E'', °F (°C)	ASTM D-4065	253 (123.3)
Tg by TMA, °F (°C)	ASTM D-3386	228 (109.4)
Compressive Strength, 0.2% offset, psi (MPa)	ASTM D-695	8,200
Compressive Modulus, psi (MPa)	ASTM D-695	350,000
Surface Roughness, fly cut, Ra/Rz		3.7/22
Coefficient of Thermal Expansion	ASTM D-3386	
-22° to 86°F, in/in/°F		19 - 21 x 10 ⁻⁶
-30° to 30°C, in/in/°C		34 - 38 x 10 ⁻⁶

* Tested @ 77°F (25°C) unless otherwise noted.

NOTE : These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed in establishing product specifications, please consult with our Product Management Department.

Use Ren-Weld 5008 adhesive for bonding. Let cure 24 hrs. @ R.T. initially. It is recommended to run tool or model through the intended application cure before final machining to the dimensions needed.

Distributed By
Freeman Manufacturing & Supply Co.
www.freemansupply.com 800-321-8511



IMPORTANT!

Post-Cure of parts on RS 5008 Tools: The temperature differential (delta T) between the center of the tool and the external surface must never exceed 50°F on either ramp up or cool down. To achieve this, a temperature soaks of 6 hours every 50°F up and down in the oven and temperature ramp rates of no more than 1°F/min are recommended, but if the temperature differential would exceed 50°F then these parameters need to be adjusted until it does not. Leave the tool in the oven for at least 6 hours below 100°F before opening doors and exposing the tool to room temperature conditions.

Use of RenShape High Performance Sealer is recommended. When used along with a release system, it greatly helps surface sealing and release.

MACHINING	Roughing Speed	Roughing Feed	Finishing Speed	Finishing Feed
	1,600 RPM	40 IPM (101cm/min.)	10,000 RPM	100 IPM (254cm/min.)

Cutters: Roughing 1 in. (2.5cm) Hog Ball End Mill 4-Flute HS Steel 8% cobalt
Finishing 5/8 in (16mm) Ball End Mill 2-Flute Carbide
Depth Roughing varies from 0.25 in. to 2.5 in. (6mm to 6.35cm) with a 40% stepover
Finishing depth is 1/8 in. (3mm) leaving a 0.002 in. (0.05mm) scallop height

These machining parameters are represented as starting points. Cutter type and material, spindle speed, feed rate, machine power and rigidity all affect machining results. User must determine the best parameters for specific situations.

STORAGE :

RenShape® 5008 boards should be stored flat in a dry place, in the sealed original container, at temperatures between +2°C and +40°C (+35.6°F and 104°F). Under these storage conditions, the shelf life is 10 years. The product should not be exposed to direct sunlight.

PRECAUTIONARY STATEMENT :

Huntsman Advanced Materials Americas LLC maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to MSDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN**FOR PROFESSIONAL**

IMPORTANT LEGAL NOTICE

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

RenShape, RenPatch and RenWeld are registered trademarks of Huntsman LLC or an affiliate thereof in one or more countries, but not all countries.

© 2014 Huntsman Advanced Materials Americas Inc.

Main Offices :
Huntsman Corporation
10003 Woodloch Forest Dr.
The Woodlands
Texas 77380
(281) 719-6000

**Huntsman Advanced Technology
Center**
8600 Gosling Rd.
The Woodlands
Texas 77381
(281) 719-7400

Distributed By
Freeman Manufacturing & Supply Co.
www.freemansupply.com 800-321-8511

