



## Advanced Materials

# RenShape® 5015 Low Density Board

### DESCRIPTION:

RenShape® 5015 board is a blue/green colored, syntactic polyurethane with a density of approximately 6 lbs./ft<sup>3</sup>. The board is easy to machine and features a good surface finish. The RenShape® 5015 board can be hand carved as well as CNC machined for the production of visual, styling and temporary master models, architectural master models, and prototypes. It is also well suited for CAD design verification.

ADVANTAGES	
	• Easy to hand-work and machine
	• Suitable for milling with fast cutting speeds
	• Non abrasive
	• Good edge definition
	• Good dimensional stability

ACCESSORIES	Matched Epoxy Adhesive	Repair Paste
	Ren-Weld® 103 , Freeman Repro Ultra Light	Freeman Quick-Fil

TYPICAL PROPERTIES*	Test Method	FTest Values
Color	Visual	Blue-Green
Density, lb./ft <sup>3</sup> (g/cm <sup>3</sup> )	ASTM D-1622	6 (0.096)
Ultimate Flexural Strength, psi (MPa)	ASTM C-203	190 (1.3)
Ultimate Tensile Strength, psi (MPa)	ASTM D-1623	160 (1.1)
Compressive Strength Parallel to Rise psi (MPa)	ASTM D-1621	148 (1.0)
Compressive Strength Perpendicular to Rise psi (MPa)		130 (0.9)
CTE	ASTM D-696	33 x 10 <sup>-6</sup> °F 59 x 10 <sup>-6</sup> °C
Service Temperature °F (°C) **	Internal	-300/+195 (-149/+91)

\* Tested @ 74°F (23°C) unless otherwise noted.

\*\* Actual service temperature limits vary considerably based on actual conditions and on client tolerance, contact us for further information.

**NOTE:** These physical properties are reported as typical test values obtained by our test laboratory. If assistance is needed in establishing product specifications, please consult with our Product Management Department.

MACHINING	Roughing Speed	Roughing Feed	Finishing Speed	Finishing Feed
	2,500 RPM	200 IPM (508cm/min)	15,000 RPM	200 IPM (508cm/min)

**Cutters:** **Roughing** 1 in. (2.5cm) Hog Ball End Mill 4-Flute HS Steel 8% cobalt  
**Finishing** 5/8 in (16mm) Ball End Mill 2-Flute Carbide  
**Depth** Roughing varies from 0.25 in. to 2.5 in. (6mm to 6.35cm) with a 40% stepover  
Finishing depth is 1/8 in. (3mm) leaving a 0.002 in. (0.05mm) scallop height

**These machining parameters are represented as starting points.** Cutter type and material, spindle speed, feed rate, machine power and rigidity all affect machining results. User must determine the best parameters for specific situations.

---

**STORAGE :**

RenShape® 5015 board should be stored flat in original cartons in a dry place at temperatures between 36°F to 104°F (2°C to 40°C). Under these storage conditions, the shelf life is 10 years. The product should not be exposed to direct sunlight.

---

**PRECAUTIONARY STATEMENT :**

Huntsman Advanced Materials Americas LLC maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

**First Aid!**

Refer to MSDS as mentioned above.

**KEEP OUT OF REACH OF CHILDREN  
FOR PROFESSIONAL**

---

**IMPORTANT LEGAL NOTICE**

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supersedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

RenShape and RenWeld are registered trademarks of Huntsman LLC or an affiliate thereof in one or more countries, but not all countries.

© 2010 Huntsman Advanced Materials Americas Inc.

Main Offices:  
**Huntsman Corporation**  
10003 Woodloch Forest Dr.  
The Woodlands  
Texas 77380  
(281) 719-6000

**Huntsman Advanced Technology  
Center**  
8600 Gosling Rd.  
The Woodlands  
Texas 77381  
(281) 719-7400