

**Advanced Materials****RenShape® BM 70 US Material****BOARD MATERIAL  
MODELLING BOARD****KEY PROPERTIES**

- Good surface finish
- Good flexural and compressive strength
- Low coefficient of thermal expansion, good dimensional stability

**APPLICATIONS**

- Master models
- Cubing models
- Patterns

**PRODUCT DATA**

<b>Product</b>	<b>Color</b>	<b>Test method</b>
RenShape® BM 70 US	Brown	visual

**PROPERTIES**

<b>Density</b>	<b>ISO 1183</b>	Lbs/ft. <sup>3</sup>	42
<b>Hardness</b>	<b>ISO 868</b>	Shore D	60-65
<b>Coefficient of thermal expansion</b>	<b>ISO 11359</b>	in/in/°F	27.7 – 30.5 x (10 <sup>-6</sup> )
<b>Deflection temperature</b>	<b>ISO 75</b>	°F	167 - 176
<b>Compressive strength</b>	<b>ISO 604</b>	Psi	2,900 – 3,600
<b>Compressive Modulus</b>		Psi	131,850 – 139,104
<b>Flexural strength</b>	<b>ISO 178</b>	Psi	3,620 – 4,340

---

---

**MILLING** Milling parameter available on request.

---

**WORKING CONDITIONS** The product should be used when in the temperature range 20° to 25°C.

---

**PACKAGING**

Dimensions	Volume (Board Ft)	Weight (lbs.)	Number of Boards (per pack)	Number of Boards (per pallet)
2" x 24" x 60"	20	70	1	36
3" x 24" x 60"	30	105	1	18
4" x 24" x 60"	40	140	1	18
6" x 24" x 60"	60	210	1	14

**STORAGE**

RenShape® BM 70 US boards should be stored flat in a dry place, at temperatures between 3506°F and 104°F. Under these storage conditions the shelf life is 10 years. The product should not be exposed to direct sunlight.

**PRECAUTIONARY STATEMENT**

Huntsman Advanced Materials Americas maintains up-to-date Material Safety Data Sheets (MSDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

**First Aid!**

Refer to MSDS as mentioned above.

**KEEP OUT OF REACH OF CHILDREN**

**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, WHETHER EXPRESS OR IMPLIED, INCLUDING BUT WITHOUT LIMITATION, AS TO MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE.

The behavior of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behavior of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behavior should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., and Huntsman Advanced Materials (Hong Kong) Ltd. Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials Americas in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

[ ] is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2010 Huntsman Corporation or an affiliate thereof. All rights reserved.

**Huntsman Advanced Materials**  
10003 Woodloch Forest Drive  
The Woodlands, Texas 77380

Tel: 888-564-9318  
Fax: 281-719-4047  
[www.huntsman.com/advanced\\_materials](http://www.huntsman.com/advanced_materials)