



BLUESIL™ V 1065

Distributed By
Freeman Manufacturing & Supply Co.
www.freemansupply.com 800-321-8511 **FREEMAN**

Condensation Cure Silicone Elastomer

Description **BLUESIL™ V 1065** is a high strength, two-component, tin catalyzed, room temperature cure silicone rubber. It is designed as a 25 Durometer (Shore A), medium viscosity rubber providing excellent physical properties, long library life and accurate detail reproduction. **BLUESIL™ V 1065** is the most popular moldmaking material in the Bluestar Silicones line

Applications

- Figurine and giftware casting using Polyester, Urethane, Plaster or Gypsum
- Furniture and Architectural Molding
- Stereolithography, prototype tooling

Typical Properties

TYPICAL PROPERTIES - AS SUPPLIED

Part A - Base Component

- **Color** White liquid
- **Consistency** Pourable
- **Viscosity**, cP. (mPa.s) 60,000

Part B - Catalyst Component (Hi-Pro Green)

- **Color** Green
- **Viscosity**, cP. (mPa.s) 90

TYPICAL CATALYZED PROPERTIES

Mixed at 24°C (75°F) and 50% R.H.

Mix Ratio A:B (Parts by weight) at 10:1

	Hi-Pro Green	Hi-Pro Blue (fast catalyst)
• Viscosity , cP. (mPa.s)	45,000	43,000
• Pot Life , hours ⁽¹⁾	5	2
• Demold Time , hrs at RT	16	6
• 24 Hour Thick Section Hardness , Shore A ⁽²⁾	27	28

TYPICAL PROPERTIES OF CURED RUBBER, Cured 7 days at 24°C (75°F) and 50% RH

Property	Test Method	Value	
		Hi-Pro Green	Hi-Pro Blue
• Color		Green	Blue
• Specific Gravity		1.11	1.11
• Hardness (Shore A)	ASTM D2240	25	30
• Tensile Strength , psi (N/mm ²)	ASTM D412	670 (4.6)	630 (4.3)
• Elongation (%)	ASTM D412	480	430
• Tear Resistance , ppi (N/mm)	ASTM D624, Die B	140 (24.6)	100 (17.5)
• Linear Shrinkage (%) ⁽³⁾	24 hours	0.2	0.5
	7 days	0.4	0.6
• Temperature Range , °C(°F)		-50 to 150 (-58 to 302)	

(1) Time at which material gels.

(2) 0.5 in. (1.27 cm) thick cup specimen.

(3) 8x8x0.25 in (20.3x20.3x0.64 cm) molded sheet, cured at room temperature

Please note: The typical properties listed in this bulletin are not intended for use in preparing specifications for any particular application of BLUESIL™ silicone materials. Please contact our Technical Service Department for assistance in writing specifications.

Instructions for use

1. Stir the base (Part A) well before use (except when machine dispensing).
2. Shake the catalyst container (Part B) well before use.
3. Weigh the desired amount of base into a clean mixing container. Tip the container and roll the base all the way around the side wall up to two inches from the top. This will prevent the catalyst from becoming absorbed into the container. It is recommended that the container be filled to not more than 1/3 the container depth to allow sufficient room for expansion during the deaeration procedure.
4. Weigh the proper amount of catalyst into the container. Mix the base and catalyst together by stirring with a stiff, flat ended metal spatula until a uniform color is obtained. Scrape the container walls and bottom well to insure a thorough mix.

Visit our website www.bluestarsilicones.com

BLUESTAR
SILICONES



Instructions for use (cont)

- Place the container into a vacuum chamber and evacuate the entrapped air from the mixture using a vacuum pump capable of achieving 29 inches of mercury vacuum. The mixture will rise, crest and then collapse in the container. Interruption (bumping) of the vacuum may be necessary to prevent overflowing the container. Keep the mixture under full vacuum for 2-3 minutes after the material has receded in the container.
- Bleed air slowly into the vacuum chamber. When the chamber is at atmospheric equilibrium, remove the cover plate and take out the container.
- Pour the deaired material slowly in a steady stream from one end of the mold box so that the material flows evenly over the pattern. This should minimize entrapment of air bubbles under the flowing material. A "print" coat may be poured first over the pattern which will also help reduce the possibility of entrapping air on the pattern and in the cured rubber. A mold release (petroleum jelly) may be applied on the pattern first to improve release.
- Allow the rubber to cure for 16-24 hours at 75±5°F (24°C) before removing the cured rubber mold from the pattern. Heat acceleration is not recommended with this product.
- For best results, allow the mold to air cure an additional 24 hours before using it in production. Full cure is achieved in 3-7 days.
- For bonding to wood or metals, use **BLUESIL™ V 04** primer. Follow recommendations on the **BLUESIL™ V 04** technical data sheet for best results.

PROCESSING INFORMATION

CATALYZED PROCESSING PROPERTIES ARE AFFECTED BY TEMPERATURE AND HUMIDITY VARIATION

- For best results, mix and cure the material at 75°F (24°C) and 50% relative humidity.
- Higher temperature and humidity will decrease the work life and pot life of the material. The faster cure will also affect the flow properties. Refrigeration of the base prior to use in hot environments has shown to improve the handling properties of this material.
- Lower temperatures and humidity will increase the work life and pot life of the material. The slower cure will increase the flow time. Cure temperatures below 68°F (20°C) are not recommended and have been found to cause a reduction in final cure hardness and properties.
- It is important that the catalyst containers are tightly closed after use. Catalyst exposed to air for extended periods of time will hydrolyze (cure). An indication of hydrolysis is a film or crust formation on the surface of the catalyst. The use of hydrolyzed catalyst is not recommended and may cause incomplete cure.

Storage and shelf life

When stored in its original unopened packaging, at a temperature of 24°C (75°F), **BLUESIL™ V 1065** may be stored for 18 months from the date of manufacture. Beyond this date, Bluestar Silicones no longer guarantees that the product meets the sales specifications.

Safety

Please consult the Safety Data Sheet. The curing agent for this material can generate a flammable gas upon contact with acidic, basic, or oxidizing materials. Precautions to avoid contact of this curing agent with these materials should be exercised. To obtain a material safety data sheet for this product contact Bluestar Silicones at 866-474-6342.

Packaging

BLUESIL™ V 1065 is available in 20 kg and 200 kg containers.

BLUESIL™ is a Trademark of **Bluestar Silicones**

 EUROPE	 NORTH AMERICA	 LATIN AMERICA	 ASIA PACIFIC
<i>Bluestar Silicones France 21 Avenue Georges Pompidou F69486 Lyon Cedex 03 FRANCE Tel. (33) 4 72 13 19 00 Fax (33) 4 72 13 19 88</i>	<i>Bluestar Silicones USA Two Tower Center Boulevard Suite 1601 East Brunswick, NJ 08816-1100 United States Tel. (1) 732 227 2060 Fax (1) 732 249 7000</i>	<i>Bluestar Silicones Brazil Ltda. Av. Maria Coelho Aguiar, 215 Bloco G - 1º Andar 05804-902 - São Paulo - SP - Brazil Tel. (55) 11 3747 7887 Fax (55) 11 3741 7718</i>	<i>Bluestar Silicones Hong Kong Trading Co. Ltd. 29th Floor, 88 Hing Fat Street Causeway Bay Hong Kong Tel. (852) 3106 8200 Fax (852) 2979 0241</i>

Warning to users

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards to infringement of or prejudice to third party rights through the use of our products. **BLUESTAR SILICONES** warrants that its products comply with its sales specifications. This information must not be used as a substitute for necessary prior tests, which ensure that a product is suitable for a given use. Determination of the suitability of product for the uses and applications contemplated by user and others shall be the sole responsibility of user. Users are responsible for ensuring compliance with local legislation and for obtaining necessary certifications and authorizations. Users are requested to ensure that they are in possession of the latest version of this document; please contact **BLUESTAR SILICONES** for the latest version and any additional information.