



**EL-325HTTC  
EPOXY COMPOSITE  
TOOLING COMPOUND**  
LIGHT-WEIGHT,  
HIGH TEMPERATURE



DISTRIBUTED BY  
**FREEMAN**  
Freeman Mfg. & Supply Co.  
www.FreemanSupply.com

**www.axson-technologies.com**  
**31200 Stephenson Hwy**

**800.344.7776**  
**Madison Heights, MI 48071**

**axsonmh@axson.com**  
**Ph 248.588.2270 Fax 248.588.5909**

**DESCRIPTION**

EL-325HTTC is an epoxy "Composite Tooling Compounds" designed for the construction of tools, jigs, models and other tooling that will see elevated temperatures. Use of EL-325HTTC allows a considerable time and labor saving in tool construction. The neutral resin and black hardener give a uniform dark gray color when thoroughly mixed that is pliable and can be applied to the tool surface without crumbling or cracking.

Tools constructed with EL-325HTTC maintain a very high degree of dimensional stability, are light weight, can be machined as well as drilled and tapped. All of these qualities allow EL-325HTTC to be used in a variety of tooling applications. EL-325HTTC offers the toolmaker a safer alternative to standard high temperature epoxy laminating systems since both resin and hardener are syntactic compounds which minimize splash hazards. EL-325HTTC does not contain MDA or VCHD however, the hardener is corrosive and gloves should be worn when handling.

**TYPICAL HANDLING CHARACTERISTICS @ 77°F (25°C)**

Mix Ratio (parts by weight) .....	100R/25H
Mix Ratio (parts by volume) .....	3.7R/1H
Specific Gravity .....	0.633 g/cc
Viscosity .....	Syntactic Dough
Work Life .....	1½ - 2 hours
Demold Time.....	16-24 hours
Peak Exotherm (1 lb mass, 6" deep).....	130°F (54°C)
Mixed Color .....	Dark gray
Shelf Life Resin & Hardener (in original unopened container).....	1 year

**TYPICAL PHYSICAL PROPERTIES (Cast Bar: 5" x ½" X ½")**

Ultimate Flexural Strength (ASTM D-790.92) .....	9,600psi (66MPa)
Flexural Modulus (ASTM D-790.92).....	540,000psi (3,723MPa)
Ultimate Compressive Strength (ASTM D-695.91).....	4,900psi (34MPa)
Coefficient of Thermal Expansion (TMA) (ppm/°F (°C)).....	9 (16)
Heat Deflection Temperature (ASTM D-648.82).....	425°F (218°C)
Exotherm( 1 lb mass, 6" deep). .....	130°F (54°C)
Hardness.....	65-70 Shore D

**APPLICATION**

Note: it will be necessary to apply a slurry mixture to be used as a bond coat between the laminate and EL-325HTTC Tooling Compound. A slurry mixture is a 50/50 by volume mixture of catalyzed EL337 or EL315 high temperature epoxy laminating resin and EL-325HTTC. This slurry helps to insure the strongest bond between laminate and EL-325HTTC tooling compound (**a product application guide is available for EL-325HTTC tooling compound applications**).

**PRELIMINARY CURE SCHEDULE:**

On Model Cure for 24 hours @ 77°F (25°C)  
+ 6 hours 150°F (66°C)

Tool support structure can be attached and tool de-molded after this schedule is completed.



**POST CURE SCHEDULE:**

After completing the Preliminary Cure Schedule, complete the following:

- 1 hour @ 200°F (93°C)
- 1 hour @ 250°F (121°C)
- 1 hour @ 300°F (149°C)
- 3 hours @ 350°F (177°C)

Thermocouples can be installed to monitor mold temperature throughout the post cure process.

**HEATING AND COOLING RATES DURING POST CURE:**

Allow tools made with ADTECH high temperature tooling resins to cure 24hrs at room temperature before subjecting them to post cure.

When oven curing laminated molds, always place mold in a room temperature oven and increase temperature at a rate of 50°F (30°C) per hour. When finished, allow molds to remain in the heated oven, decreasing temperature at a rate of 50°F (30°C) per hour. Never remove the mold from the oven until temperature has been lowered to less than 100°F (38°C).

EL-325HTTC Tech/Revised 1/7/15  
Supersedes 5/20/14

The information contained in this technical data sheet results from research and tests conducted in our laboratories under precise conditions. Seller cannot anticipate all conditions under which seller's products, or the products of other manufacturers in combination with seller's products, may be used. It is the responsibility of the user to determine the suitability of the Axson Technologies' products, under their own conditions, before commencing with the proposed application. In no event shall Axson Technologies, Inc. be liable for any direct, indirect, punitive, incidental, special, and/or consequential damages, to property or life, whatsoever arising out of or connected with the use or misuse of our products.

<b>AXSON TECHNOLOGIES US</b> +1 248 588 2270 axsonmh@axson.com axson-na.com	<b>CHINA</b> +86 21 58 68 30 37 marketing.china@axson.com <b>MEXICO</b> +52 55 52 64 49 22 marketing@axson.com.mx	<b>GERMANY</b> +49 6 07 44 07 11-0 verkauf@axson.com <b>MIDDLE EAST</b> +971 7 2432227 axsonmideast@axson.com	<b>INDIA</b> +91 20 25 56 07 10-11 info.india@axson.com <b>SLOVAKIA</b> +42 1 76 42 25 26 axson.sk@axson.com	<b>ITALY</b> +39 02 96 70 23 36 axson@axson.it <b>SPAIN</b> +34 9 32 25 16 20 spain@axson.com	<b>JAPAN</b> +81 5 64 26 25 91 sales.japan@axson.com <b>U.K.</b> +44 16 38 66 00 62 sales.uk@axson.com	<b>FRANCE</b> <b>Global Headquarters</b> +33 1 34 40 34 60 axson@axson.com axson-technologies.com
--	--	--	---	--	---	---