



## IsoMold UMR 411

### PRODUCT DESCRIPTION

Isotec's IsoMold UMR 411 (Formerly PAM 2140) is used to make molds of detailed masters that contain shallow undercuts. Some of the most common uses of IsoMold UMR 411 are concrete formliners and to make molds for point-of-purchase displays, rapid prototypes, special effects, taxidermy, and sculpture reproductions. IsoMold UMR 411 is a two-part polyurethane molding system. IsoMold UMR 411 is mixed one-to-one by and cures at room temperature. IsoMold UMR 411 cures to a medium hardness (Shore A40± 2), light to medium amber rubber.

### APPLICATIONS

Point of Purchase Displays  
Special Effects  
Sculpture Reproductions

Rapid Prototypes  
Taxidermy

### REACTION PROFILE

Ratio by Weight (iso:polyol) :	105 - 100	
Ratio by Volume (iso:polyol) :	1 - 1	
Pot Life (100g) :	15	Minutes
Rise Time :	15 - 16	Minutes
DeMold Time :	24	Hours
Cure Time :	5	Days
Mix Time :	1 - 2	Minutes

### COMPONENT PROPERTIES

Color, Isocyanate :	clear	
Color, Polyol :	clear	
Specific Gravity (74F), Isocyanate :	1.051	
Specific Gravity (74F), Polyol :	1.00	
Viscosity (74F), ASTM D-1638 (ISO) :	1100	cps
Viscosity (74F), ASTM D-1638 (Polyol) :	350	cps





## IsoMold UMR 411

### TYPICAL PHYSICAL PROPERTIES

Shore Hardness- A, ASTM D2240 :	38 - 42	
Tear, Die C :	90	pli
Split Tear, ASTM D470 :	18	pli
Elongation, ASTM D412 :	600	%
Rebound Bashore %, ASTM D2632 :	60	
Compound Specific Gravity :	1.026	





## IsoMold UMR 411

\*Values given are not intended to be used in specific preparation

### RECOMMENDED HANDLING INSTRUCTIONS

#### Instructions for Use

##### Prepare Master and Mold Housing

First, clean and dry your master thoroughly. If the master has a porous surface (clay, concrete, plaster, etc.) or is made of sulfur-based clay, you must seal it. You can use polyurethane varnish, polyurethane sealant, or paste wax to seal your master. Next, anchor your master and seal the base so that IsoMold UMR 411 does not leak under your master. A hot glue gun works to anchor and seal the base at the same time. Also, you should seal all of your mold housing connections with sulfur-free clay or hot glue. Then, apply an appropriate release agent (we recommend IsoKote™ 1000) to the master and interior of the mold housing. Apply release agent sparingly, while coating all surfaces of the master. Too much release agent may cover the details of the master. You should allow the release agent to dry approximately 10 minutes before you pour your mold.

##### Measure Curative and Prepolymer

Note: IsoMold UMR 411 provides approximately 15 minutes for you to mix and pour the mold before it begins to gel. Make sure that curative and prepolymer are room temperature before mixing them. Please note that in cold weather it may take up to 24 hours for the curative and prepolymer to reach room temperature. Using two clean, dry, plastic containers of equal size, measure equal amounts of the curative (part A) and the prepolymer (part B).

##### Mix Curative and Prepolymer

After you prepare the master and mold housing and measure the curative and prepolymer, you are ready to pour the curative and prepolymer into another clean, dry, plastic container. Scrape the curative and prepolymer containers to move all of the material into the mixing container. Combine the two ingredients for several minutes until no color striations are visible. Be sure to scrape the sides and bottom of the mixing container while combining the two ingredients. You must mix the curative and prepolymer completely so that IsoMold UMR 411 will cure correctly. If air bubbles form during mixing, you should degas the mixture to remove them.

##### Pour Mold

To ensure that no air bubbles form over the details of your master, you can brush a thin base coat onto the master and then pour the rest of the URP 4103. The best way to pour a mold is to tilt your mold slightly and pour into one spot at the corner of the mold, allowing the material to cover your master slowly like the flow of lava. When you have finished pouring the mold, you may lightly spray release agent on the top of IsoMold UMR 411 to break any air bubbles that have risen.

##### Demold and Cure Mold

Once you have poured your mold, allow the mold to cure 16 hours before demolding. To prolong the life of the mold, allow it to cure for 3–4 days before using it.

Keep the IsoMold UMR 411 container tightly closed when not in use and store at temperatures between 60–90° F (16–32° C). Do not expose the curative or prepolymer to moisture! If moisture contaminates IsoMold UMR 411, it will

Date Modified 4/8/2013



## IsoMold UMR 411

not cure. If these storage requirements are met, IsoMold UMR 411 carries a shelf life warranty of six months.

Be sure to read the Material Safety Data Sheet that comes with IsoMold UMR 411. When working with IsoMold UMR 411 please observe the following safety precautions.

- Use only in well-ventilated areas.
- Wear safety glasses, chemical-resistant rubber or plastic gloves, and an apron.
- Avoid prolonged or repeated contact with skin.
- In the case of skin contact, wipe affected area with isopropyl alcohol, followed by soap and water.
- In the case of eye contact, flush eyes with water for 15 minutes and consult a physician.
- If swallowed, drink one to two glasses of water and seek medical attention immediately.

### SAFETY

Please refer to the IsoMold UMR 411 SDS for complete information on safe use and handling of this product. When working with IsoMold UMR 411, please observe the following safety precautions.

- ~~U~~se only in well-ventilated areas. Wear chemically resistant rubber gloves, safety glasses/goggles, and an apron or other protective clothing.
- ~~A~~void prolonged or repeated contact with skin.
- ~~I~~n case of skin contact, wipe affected area with isopropyl alcohol, followed by soap and water.
- ~~I~~n case of eye contact, flush eyes with water for 15 minutes and consult a physician.
- ~~I~~f swallowed or comes into contact with eyes, seek medical attention immediately.

Please refer to the MSDS for all appropriate health and safety information.

---

Since Seller exercises no control over Buyer's application or use of the product manufactured by Seller ("product") and since materials used with the product may vary, it is understood that:

- THERE ARE NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FOR ANY PARTICULAR PURPOSE.) While all data presented in Seller's technical data sheet is based on the best information available to Seller and believed correct, such data is not to be construed as a warranty that the product will conform to such specifications. Such technical data sheets are subject to change without notice. Reported laboratory test results of fire redundancy in no way relates to the actual performance under fire conditions. Since all urethane systems are organic, they will burn.
- Reported laboratory test results of the color stability in no way relates to the actual performance upon exposure to light sources. Since all aromatic urethanes experience color degradation upon ultraviolet light exposure, Seller shall not be liable for any damages resulting from ultraviolet light color degradation of any aromatic urethane systems manufactured or sold by Seller.
- The liability of the Seller shall not exceed the purchase price and the Buyer shall not be entitled to nor the Seller be liable for any consequential, incidental, indirect or special damages resulting in any manner from the furnishing of the product.

