



RenCast 6401 Surface Coat

Description

RenCast 6401 may be thickened to use as a surface coat using the Freeman 1060 Hardener as a third component thickening agent.

Procedure

First determine the required amount of Freeman 1060 Thickening Agent to use by multiplying the amount of Ren 6401 hardener being used by 0.005 if you want a thin gel coat consistency or by 0.030 if you want a thicker buttery consistency.

Example: For thin consistency, you would add 0.5 grams of 1060 Thickening Agent per 100 grams of the Ren 6401 hardener. Or for thicker consistency, you would add 3 grams of 1060 Thickening Agent per 100 grams of Ren 6401 hardener.

Once required amount of thickening agent has been determined add the Freeman 1060 Thickening Agent to the hardener side of the RenCast 6401 and mix thoroughly, making sure there are no unmixed areas. Lumps may result in surface coat if not mixed thoroughly.

Next weigh out the amount of resin you would normally use, plus an additional amount of resin equal to that of the thickening agent used.

Example: RenCast 6401 has a mix ratio of 25:100, resin to hardener by weight. If you were to add 3 grams of 1060 Thickening Agent to 100 grams of Ren 6401 Hardener, then the required amount of RenCast 6401 resin would be the required 25 grams plus equal amount of 1060 Thickening Agent used which would be 3 grams for a total of 28 grams of RenCast 6401 resin.

Mix the resin and the hardener together thoroughly. Try not to blend in air. This mixture will quickly begin to thicken and will be ready for application after 2-3 minutes.

Ordering Information

SKU	Description	Size	Net wt.
056926	RenCast 6401-3 Unit (Resin & Hardener)	Gallon Kit	10 lbs.
056528	RenCast 6401-1 Resin Only	2 Quarts	9 lbs.
056924	Ren 6401-3 Hardener Only	5-Gallon	36 lbs.
055106B	Freeman 1060 Black Hardener (Thickening Agent)	1-Gallon	3.7 Lbs.
055110B	Freeman 1060 Red Hardener (Thickening Agent)	1-Gallon	3.7 lbs.

The user shall determine the suitability of this product for their application and assumes all risks and liabilities associated with the use of this product. The exclusive remedy for all proven claims is replacement of our materials only and in no event shall Freeman Mfg. & Supply Co. be liable for special, incidental, or consequential claims.

READ SAFETY DATA SHEETS AND PRODUCT LABELS BEFORE USING PRODUCT