



Technical Data Sheet

RenCast 6443 Surface Coat

Description

RenCast 6443 may be thickened to use as a surface coat using the RenCast 6400-1 Resin as a third component thickening agent.

Procedure

First determine the required amount of RenCast 6400-1 Thickening Agent to use by multiplying the amount of RenCast 6443 Resin being used by 0.005 for a thin consistency or by 0.030 for a thicker buttery consistency.

Example: For thin consistency, you would add 0.5 grams of RenCast 6400-1 Thickening Agent per 100 grams of the RenCast 6443 Resin. Or for thicker consistency, you would add 3 grams of RenCast 6400-1 Thickening Agent per 100 grams of RenCast 6443 Resin.

Once required amount of thickening agent has been determined add the RenCast 6400-1 Thickening Agent to the resin side of the RenCast 6443 and mix thoroughly, making sure there are no unmixed areas. Lumps may result in surface coat if not mixed thoroughly.

Next weigh out the amount of hardener you would normally use, plus an additional amount of hardener 2X that of the thickening agent used.

Example: RenCast 6443 has a mix ratio of 100:60, resin to hardener by weight. If you were to add 3 grams of 6400-1 Thickening Agent to 100 grams of RenCast 6443 Resin, then the required amount of Ren 6443 hardener would be the required 60 grams plus 2X the amount of 6400-1 Thickening Agent used for a total of 66 grams of Ren 6443 hardener. Mix the resin and the hardener together thoroughly. Try not to blend in air. This mixture will quickly begin to thicken and will be ready for application after 2-3 minutes.

Ordering Information

SKU	Description	Size	Net wt.
056545	RenCast 6443 Unit (Resin & Hardener)	Gallon Kit	11.2 lbs.
056546	RenCast 6443 Resin Only	5-Gallon	40 lbs.
056547	Ren 6443 Hardener Only	5-Gallon	24 lbs.
056548	RenCast 6400-1 Thickening Agent	Pint	.5 lbs.

The user shall determine the suitability of this product for their application and assumes all risks and liabilities associated with the use of this product. The exclusive remedy for all proven claims is replacement of our materials only and in no event shall Freeman Mfg. & Supply Co. be liable for special, incidental, or consequential claims.

READ SAFETY DATA SHEETS AND PRODUCT LABELS BEFORE USING PRODUCT