

Ren[®] and Other Repair Materials Specifications

Product Number	Mix Ratio Resin to Hrd'nr by wt.	Gel Time (min)	Hardness (Shore D)	Mixed Viscosity Brookfield (cps.)	Density (g/cc)	Coefficient Of Thermal Expansion (in./in./°F)	Color
Ren Patch 5008	100:21	15	68	Paste	-	1.8×10^{-5}	Light Blue
Ren Patch 5169	100:86	45-75 sec	>85	Paste	1.2	4.26×10^{-5}	Red
TDT 177-113	100:82	20	63	Paste	0.68	3.46×10^{-5}	
Maxim Fast	1:1	5	-	Paste	1.32	-	Black
Lab-Metal	-	-	81	Paste	1.95	1.5×10^{-5}	Gray
Dynalite	100:1.5	6	69	360,000	1.21	-	Light Peach
Dyna-Plus	100:1.5	4	60	245,000	1.36	-	Gold
ASTM		D2471	D2240	D2393	D792	D3386	

©2002-6 Freeman Mfg. & Supply Co.

Please read our disclaimer at www.freemansupply.com/disclaimer.htm